

THE CHEMICAL FORMULARY

The Chemical Formulary

*A Collection of Valuable, Timely, Practical,
Commercial Formulae and Recipes for
Making Thousands of Products in
Many Fields of Industry*

VOLUME XI

Editor-in-Chief

H. BENNETT

Technical Director, Cheminform Institute



1961

CHEMICAL PUBLISHING CO., INC.

212 FIFTH AVENUE

NEW YORK, N. Y.

© 1961 BY H. BENNETT

PRINTED IN THE UNITED STATES OF AMERICA

Editor-in-Chief

H. BENNETT

Board of Editors

| | |
|------------------|-------------------------------------|
| Addison, H. D. | Pro-phy-lac-tic Brush Co. |
| Allen, A. O. | Vita-Var Corp. |
| Arenson, S. W. | Food Research Laboratory |
| Bowman, C. E. | Industrial Chemist |
| Boynton, M. S. | U. S. Army Medical Labs. |
| Cahn, H. L. | U. S. Stoneware Co. |
| Carleton, R. K. | Boston College |
| Carpenter, J. M. | Western Chemical Co. |
| Donner, Howard | Consultant |
| Du Bois, A. S. | West Disinfecting Co. |
| Eisen, J. | Schwarz Drug Stores, Inc. |
| Friedman, A. I. | Mt. Sinai Hospital |
| Goldschmiedt, H. | Mem Co. |
| Gould, D. E. | Consultant |
| Hathorne, B. L. | Textile Specialist |
| Holst, W. A. | National Aniline Division |
| Hopton, A. W. | Niagara Industrial Labs. |
| Hoyt, L. F. | National Aniline Division |
| Jones, H. I. | Hizone Labs. |
| Kamlet, J. | Kamlet Laboratory |
| Kampf, L. | New York City Bureau of Engineering |
| Kerr, T. J. | Plastic Consultant |
| Klein, H. | Consultant |
| Klein, Samuel | Licensed Food and Drug Inspector |
| Kulakow, S. E. | Hodag Chemical Co. |
| Lawton, L. M. | Harrison Radiator Division |
| Lazzaro, V. C. | Research Chemist |
| Levey, H. A. | Chemical Engineering Counselor |
| Levitt, B. | Curley Co. |
| Lustbader, M. H. | Autographic Register Co. |
| Maglio, M. M. | Worth Labs. |

| | |
|--------------------|-------------------------------------|
| Mathers, F. C. | Indiana University |
| Metro, F. G. | Consulting Chemist |
| Meyer, G. | Eastman Kodak Co. |
| Migliaresi, J. | Pure Carbon Co. |
| Mohler, J. B. | Johnson Bronze Co. |
| Opp, C. J. | Interchemical Corp. |
| Owades, J. L. | College of City of New York |
| Pact, H. | Glyco Products Co. |
| Polis, J. E. | Development Chemist |
| Reynolds, M. M. | Reynolds Associates |
| Rose, R. J. | Consultant |
| Seiden, R. | Consultant |
| Seymour, R. B. | Atlas Mineral Products Co. |
| Sheers, E. H. | American Cyanamid Co. |
| Shepherd, H. R. | Connecticut Chemical Research Corp. |
| Sirota, J. | Cathodium Metallizing Co. |
| Stout, A. W. | Western Pine Association |
| Turer, J. | Virginia-Carolina Chemical Corp. |
| Van der Scheer, J. | Consulting Chemical Engineer |
| Werner, J. | General Aniline & Film Corp. |
| Whitener, P. D. | Winthrop College |
| Wolf, R. F. | Columbia-Southern Chemical Corp. |
| Yamins, J. L. | National Dairy Research Labs. |
| Zeih, C. J. de | Argonne National Laboratory. |

P R E F A C E

Chemistry, as taught in our schools and colleges, concerns chiefly synthesis, analysis, and engineering — and properly so. It is part of the right foundation for the education of the chemist.

Many a chemist entering an industry soon finds that most of the products manufactured by his concern are not synthetic or definite chemical compounds, but are mixtures, blends, or highly complex compounds of which he knows little or nothing. The literature in this field, if any, may be meager, scattered, or obsolete.

Even chemists with years of experience in one or more industries spend considerable time and effort in acquainting themselves with any new field which they may enter. Consulting chemists similarly have to solve problems brought to them from industries foreign to them. There was a definite need for an up-to-date compilation of formulae for chemical compounding and treatment. Since the fields to be covered are many and varied, an editorial board of chemists and engineers engaged in many industries was formed.

Many publications, laboratories, manufacturing firms, and individuals have been consulted to obtain the latest and best information. It is felt that the formulae given in this volume will save chemists and allied workers much time and effort.

Manufacturers and sellers of chemicals will find, in these formulae, new uses for their products. Nonchemical executives, professional men, and interested laymen will make through this volume a “speaking acquaintance” with products which they may be using, trying, or selling.

It often happens that two individuals using the same ingredients in the same formula get different results. This may be due to slight deviations in the raw materials or unfamiliarity with the intricacies of a new technique. Accordingly, repeated experiments may be

necessary to get the best results. Although many of the formulae given are being used commercially, many have been taken from the literature and may be subject to various errors and omissions. This should be taken into consideration. Wherever possible, it is advisable to consult with other chemists or technical workers regarding commercial production. This will save time and money and help avoid trouble.

A formula will seldom give exactly the results which one requires. Formulae are useful as starting points from which to work out one's own ideas. Also, formulae very often give us ideas which may help us in our specific problems. In a compilation of this kind, errors of omission, commission, and printing may occur. I shall be glad to receive any constructive criticism.

H. BENNETT

PREFACE TO VOLUME XI

This new volume of the CHEMICAL FORMULARY series is a collection of new, up-to-date formulae. The only repetitious material is the introduction (Chapter I) which is used in every volume for the benefit of those who may have bought only one volume and who have no educational background or experience in chemical compounding. The simple basic formulae and compounding methods given in the introduction will serve as a guide for beginners and students. It is suggested that they read the introduction carefully and even make a few preparations described there before compounding the more intricate formulae included in the later chapters.

The list of chemicals and their suppliers has been enlarged with new trade-mark chemicals, so that buying the required ingredients will present no problem.

Grateful acknowledgement is made to the Board of Editors for their valuable suggestions and contributions.

H. BENNETT

NOTE: All the formulae in volumes I, II, III, IV, V, VI, VII, VIII, IX, X, and XI (except in the introduction) are different. Thus, if you do not find what you are looking for in this volume, you may find it in one of the others.

NOTE: This book is the result of cooperation of many chemists and engineers who have given freely of their time and knowledge. It is their business to act as consultants and to give advice on technical matters for a fee. As publishers, we do not maintain a laboratory or consulting service to compete with them. Therefore, please do not ask *us* for advice or opinions, but confer with a chemist.

Formulae for which patent numbers are listed can be manufactured only after obtaining a license from the patentees.

CONTENTS

| | <i>Page</i> |
|---|-------------|
| PREFACE | 7 |
| PREFACE TO VOLUME XI | 9 |
| ABBREVIATIONS | 11 |
| <i>Chapter</i> | |
| I INTRODUCTION | 13 |
| II ADHESIVES | 41 |
| III CERAMICS AND GLASS | 70 |
| IV COSMETICS AND DRUGS | 74 |
| V EMULSIONS | 124 |
| VI FARM AND GARDEN PRODUCTS | 138 |
| VII FOOD PRODUCTS | 141 |
| VIII INKS | 146 |
| IX INSECTICIDES, FUNGICIDES, AND WEED KILLERS | 153 |
| X LEATHER, SKINS, AND FURS | 169 |
| XI LUBRICANTS | 172 |
| XII MATERIALS OF CONSTRUCTION | 178 |
| XIII METALS AND THEIR TREATMENT | 181 |
| XIV PAINT, VARNISH, AND LACQUER | 217 |
| XV PAPER | 237 |
| XVI PHOTOGRAPHY | 254 |
| XVII POLISHES | 258 |
| XVIII PYROTECHNICS AND EXPLOSIVES | 284 |
| XIX RUBBER, RESINS, PLASTICS, AND WAXES | 286 |
| XX SOAPS AND DETERGENTS | 308 |
| XXI TEXTILES | 343 |
| XXII APPENDIX: | |
| Tables | 356 |
| References and Acknowledgments | 364 |
| Trade-Mark Chemicals | 365 |
| Chemicals and Supplies: Where To Buy Them | 366 |
| Sellers of Chemicals and Supplies | 391 |
| INDEX | 405 |

ABBREVIATIONS

| | |
|----------------------|------------------------------|
| amp. | ampere |
| amp./dm ₂ | amperes per square decimeter |
| amp./sq. ft. | amperes per square foot |
| anhydr. | anhydrous |
| avoir. | avoirdupois |
| bb. | barrel |
| Bé. | Baumé |
| B.P. | boiling point |
| °C | degrees Centigrade |
| cc. | cubic centimeter |
| c.d. | current density |
| cm. | centimeter |
| cms. | cubic centimeter |
| conc. | concentrated |
| c.p. | chemically pure |
| cp. | centipoise |
| cu. ft. | cubic foot |
| cu. in. | cubic inch |
| cwt. | hundredweight |
| d. | density |
| dil. | dilute |
| dm. | decimeter |
| dm ² | square decimeter |
| dr. | dram |
| E. | Engler |
| °F. | degrees Fahrenheit |
| f.f.c. | free from chlorine |
| f.f.p.a. | free from prussic acid |
| fl. dr. | fluid dram |
| fl. oz. | fluid ounce |
| fl. pt. | flash point |
| F.P. | freezing point |
| ft. | foot |
| ft ² | square foot |
| g. | gram |

| | |
|-------------|-------------------------------|
| gal..... | gallon |
| gr..... | grain |
| hl..... | hectoliter |
| hr..... | hour |
| in..... | inch |
| kg..... | kilogram |
| l..... | liter |
| lb..... | pound |
| liq..... | liquid |
| m..... | meter |
| min..... | minim; minute |
| ml..... | milliliter (cubic centimeter) |
| mm..... | millimeter |
| M.P..... | melting point |
| N..... | Normal |
| N.F..... | National Formulary |
| oz..... | ounce |
| pH..... | hydrogen-ion concentration |
| p.p.m..... | parts per million |
| pt..... | pint |
| pwt..... | pennyweight |
| q.s..... | a quantity sufficient to make |
| qt..... | quart |
| r.p.m..... | revolutions per minute |
| sec..... | second |
| sp..... | spirits |
| Sp. Gr..... | specific gravity |
| sq. dm..... | square decimeter |
| tech..... | technical |
| tinc..... | tincture |
| tr..... | tincture |
| Tw..... | Twaddell |
| U.S.P..... | United States Pharmacopeia |
| v..... | volt |
| visc..... | viscosity |
| vol..... | volume |
| wt..... | weight |

CHAPTER I

INTRODUCTION

The following introductory matter has been included at the suggestion of teachers of chemistry and home economics.

This section will enable anyone, with or without technical education or experience, to start making simple products without any complicated or expensive machinery. For commercial production, however, suitable equipment is necessary.

Chemical specialties are composed of pigments, gums, resins, solvents, oils, greases, fats, waxes, emulsifying agents, dyestuffs, perfumes, water, and chemicals of great diversity. To compound certain of these with some of the others requires definite and well-studied procedures, any departure from which will inevitably result in failure. The steps for successful compounding are given with the formulae. Follow them rigorously. If the directions require that (*a*) is added to (*b*), carry this out literally, and do not reverse the order. The preparation of an emulsion is often quite as tricky as the making of mayonnaise. In making mayonnaise, you add the oil to the egg, slowly, with constant and even stirring. If you do it correctly, you get mayonnaise. If you depart from any of these details: If you add the egg to the oil, or pour the oil in too quickly, or fail to stir regularly, the result is a complete disappointment. The same disappointment may be expected if the prescribed procedure of any other formulation is violated.

The point next in importance is the scrupulous use of the proper ingredients. Substitutions are sure to result in inferior quality, if not in complete failure. Use what the formula calls for. If a cheaper

product is desired, do not prepare it by substituting a cheaper ingredient for the one prescribed: use a different formula. Not infrequently, a formula will call for an ingredient which is difficult to obtain. In such cases, either reject the formula or substitute a similar substance only after a preliminary experiment demonstrates its usability. There is a limit to which this rule may reasonably be extended. In some cases, substitution of an equivalent ingredient may be made legitimately. For example, when the formula calls for white wax (beeswax), yellow wax can be used, if the color of the finished product is a matter of secondary importance. Yellow beeswax can often replace white beeswax, making due allowance for color, but paraffin wax will not replace beeswax, even though its light color seems to place it above yellow beeswax.

And this leads to the third point: the use of good-quality ingredients, and ingredients of the correct quality. Ordinary lanolin is not the same thing as anhydrous lanolin. The replacement of one with the other, weight for weight, will give discouragingly different results. Use exactly what the formula calls for: if you are not acquainted with the substance and you are in doubt as to just what is meant, discard the formula and use one you understand. Buy your chemicals from reliable sources. Many ingredients are obtainable in a number of different grades: if the formula does not designate the grade, it is understood that the best grade is to be used. Remember that a formula and the directions can tell you only part of the story. Some skill is often required to attain success. Practice with a small batch in such cases until you are sure of your technique. Many examples can be cited. If the formula calls for steeping quince seed for 30 minutes in cold water, steeping for 1 hour may yield a mucilage of too thin a consistency. The originator of the formula may have used a fresher grade of seed, or his conception of what "cold" water means may be different from yours. You should have a feeling for the right degree of mucilaginousness, and if steeping the seed for 30 minutes fails to produce it, steep them longer until you get the right kind of mucilage. If you do not know what the right kind is, you will have to experiment until you find out. This is the reason for the recommendation to make small experimental batches until successful results are obtained. Another case is the use of

dyestuffs for coloring lotions and the like. Dyes vary in strength; they are all very powerful in tinting value; it is not always easy to state in quantitative terms how much to use. You must establish the quantity by carefully adding minute quantities until you have the desired tint. Gum tragacanth is one of those products which can give much trouble. It varies widely in solubility and bodying power; the quantity listed in the formula may be entirely unsuitable for your grade of tragacanth. Therefore, correction is necessary, which can be made only after experiments with the available gum.

In short, if you are completely inexperienced, you can profit greatly by experimenting. Such products as mouth washes, hair tonics, and astringent lotions need little or no experience, because they are, as a rule, merely mixtures of simple liquid and solid ingredients, which dissolve without difficulty and the end product is a clear solution that is ready for use when mixed. However, face creams, tooth pastes, lubricating greases, wax polishes, etc., whose formulation requires relatively elaborate procedure and which must have a definite final viscosity, need some skill and not infrequently some experience.

Figuring

Some prefer proportions expressed by weight or volume, others use percentages. In different industries and foreign countries different systems of weights and measures are used. For this reason, no one set of units could be satisfactory for everyone. Thus divers formulae appear with different units, in accordance with their sources of origin. In some cases, parts are given instead of percentage or weight or volume. On the pages preceding the index, conversion tables of weights and measures are listed. These are used for changing from one system to another. The following examples illustrate typical units:

EXAMPLE NO. 1

Ink for Marking Glass

| | | | |
|---------------------|----|------------------|----|
| Glycerin | 40 | Ammonium Sulfate | 10 |
| Barium Sulfate | 15 | Oxalic Acid | 8 |
| Ammonium Bifluoride | 15 | Water | 12 |

Here no units are mentioned. In this case, it is standard practice

to use parts by weight throughout. Thus here we may use ounces, grams, pounds, or kilograms as desired. But if ounces are used for one item, the ounce must be the unit for all the other items in the formula.

EXAMPLE No. 2

Flexible Glue

| | | | |
|----------------|--------|----------|--------|
| Powdered Glue | 30.90% | Glycerin | 5.15% |
| Sorbitol (85%) | 15.45% | Water | 48.50% |

Where no units of weight or volume, but percentages are given, forget the percentages and use the same method as given in Example No. 1.

EXAMPLE No. 3

Antiseptic Ointment

| | | | |
|----------------|----------|--------------|--------|
| Petrolatum | 16 parts | Benzoic Acid | 1 part |
| Coconut Oil | 12 parts | Chlorothymol | 1 part |
| Salicylic Acid | 1 part | | |

The instructions given for Example No. 1 also apply to Example No. 3. In many cases, it is not wise to make up too large a quantity of a product before making a number of small batches to first master the necessary technique and also to see whether the product is suitable for the particular purpose for which it is intended. Since, in many cases, a formula may be given in proportions as made up on a factory scale, it is advisable to reduce the quantities proportionately.

EXAMPLE No. 4

Neutral Cleansing Cream

| | | | |
|-----------------------|--------|----------|---------|
| Mineral Oil | 80 lb. | Water | 90 lb. |
| Spermaceti | 30 lb. | Glycerin | 10 lb. |
| Glyceryl Monostearate | 24 lb. | Perfume | To suit |

Here, instead of pounds, ounces or even grams may be used. This formula would then read:

| | | | |
|-----------------------|-------|----------|---------|
| Mineral Oil | 80 g. | Water | 90 g. |
| Spermaceti | 30 g. | Glycerin | 10 g. |
| Glyceryl Monostearate | 24 g. | Perfume | To suit |

Reduction in bulk may also be obtained by taking the same fractional part or portion of each ingredient in a formula. Thus in the following formula:

EXAMPLE NO. 5

Vinegar Face Lotion

| | | | |
|-------------------|----|---------|-----|
| Acetic Acid (80%) | 20 | Alcohol | 440 |
| Glycerin | 20 | Water | 500 |
| Perfume | 20 | | |

We can divide each amount by ten and then the finished bulk will be only one tenth of the original formula. Thus it becomes:

| | | | |
|-------------------|---|---------|----|
| Acetic Acid (80%) | 2 | Alcohol | 44 |
| Glycerin | 2 | Water | 50 |
| Perfume | 2 | | |

Apparatus

For most preparations, pots, pans, china, and glassware, which are used in every household, will be satisfactory. For making fine mixtures and emulsions, a malted-milk mixer or egg beater is necessary. For weighing, a small, low-priced scale should be purchased from a laboratory-supply house. For measuring fluids, glass graduates or measuring glasses may be purchased from your local druggist. Where a thermometer is necessary, a chemical thermometer should be obtained from a druggist or chemical-supply firm.

Methods

To understand better the products which you intend to make, it is advisable that you read the complete section covering such products. You may learn different methods that may be used and also to avoid errors which many beginners are prone to make.

Containers for Compounding

Where discoloration or contamination is to be avoided, as in light-colored, or food and drug products, it is best to use enameled or earthenware vessels. Aluminum is also highly desirable in such cases, but it should not be used with alkalis as these dissolve and corrode aluminum.

Heating

To avoid overheating, it is advisable to use a double boiler when

temperatures below 212°F. (temperature of boiling water) will suffice. If a double boiler is not at hand, any pot may be filled with water and the vessel containing the ingredients to be heated placed in the water. The pot may then be heated by any flame without fear of overheating. The water in the pot, however, should be replenished from time to time; it must not be allowed to "go dry." To get uniform higher temperatures, oil, grease, or wax is used in the outer container in place of water. Here, of course, care must be taken to stop heating when thick fumes are given off as these are inflammable. When higher uniform temperatures are necessary, molten lead may be used as a heating medium. Of course, with chemicals which melt uniformly and are nonexplosive, direct heating over an open flame is permissible, with stirring, if necessary.

Where instructions indicate working at a certain temperature, it is important to attain the proper temperature not by guesswork, but by the use of a thermometer. Deviations from indicated temperatures will usually result in spoiled preparations.

Temperature Measurement

In the United States and in Great Britain, the Fahrenheit scale of temperature is used. The temperature of boiling water is 212° Fahrenheit (212°F.); the temperature of melting ice is 32° Fahrenheit (32°F.).

In scientific work, and in most foreign countries, the Centigrade scale is used, on which the temperature of boiling water is 100° Centigrade (100°C.) and the temperature of melting ice is 0° Centigrade (0°C.).

The temperature of liquids is measured by a glass thermometer. This is inserted as deeply as possible in the liquid and is moved about until the temperature reading remains steady. It takes a short time for the glass of the thermometer to reach the temperature of the liquid. The thermometer should not be placed against the bottom or side of the container, but near the center of the liquid in the vessel. Since the glass of the thermometer bulb is very thin, it breaks easily when striking it against any hard surface. A cold thermometer should be warmed gradually (by holding it over the surface of a hot liquid) before immersion. Similarly the hot thermometer when taken out

- | | | | |
|--------------------------------------|--------------------|-----------------------------------|--------------------|
| Abbreviations | 11 | Glass to Glass | 52 |
| Abrasive, Metal | 233 | Hot-Melt | 45, 51, 52, 53, 54 |
| Vehicle, Oil | 277 | Inorganic | 69 |
| Absorbent, Floor Oil | 327 | Interior Car Trim | 65 |
| Acaricide | 165 | Label | 52 |
| Acetate, Printing Emulsions for | 346 | Laminating | 54 |
| "Acrilan", Dyeing | 348 | Leather to Cloth | 41, 45 |
| Size | 354 | Leather to Paper | 41, 45 |
| Acrylic Yarn Sizing | 354 | Metal to Cloth | 41, 45, 52 |
| Adhesion, Increasing | 62 | Metal to Paper | 41, 45, 52 |
| Adhesive. See also Cement and Paste. | | Metal to "Paracril" | 63 |
| Agricultural Spray | 161 | Multipurpose | 51 |
| Aluminum Foil | 52 | Noncuring | 60 |
| Asphalt to Aggregate | 62 | Non-Staining | 58 |
| Asphalt to Vinyl | 52 | Nylon Fabric | 65 |
| Bag-Seam | 56 | Optical Crystal | 61 |
| Belt | 45 | Palletizing | 51 |
| Box-Top | 52 | "Paracril" | 59 |
| Carpet-Scrim | 66 | "Paracril" to Metal | 63 |
| Cellulose Acetate to Paper | 52 | Plastics | 59, 61 |
| Chipboard to Aluminum | 52 | Polyethylene | 57 |
| Cloth. See Fabric. | | Polyethylene to Paper | 59 |
| Core | 51 | Polystyrene | 57 |
| Corrugating | 49 | Pressure-Sensitive | 52, 59 |
| "Dacron" to Rubber | 65 | Quicksetting | 58 |
| Dielectric | 58 | Rubber to "Dacron" | 65 |
| Dust Filter | 57 | Bronze Bearing | 196 |
| Electrically Conducting | 69 | Chromium-Manganese Welding | 194 |
| Emulsion | 47, 52 | Copper Casting | 196 |
| Fabric to Aluminum | 52 | Corrosion Resistant Thermostatic | 205 |
| Self-Curing | 60 | Dental | 197 |
| Shoe | 49, 61 | Electric Fuse | 199, 205 |
| Silicate | 61 | Electric Resistance | 197, 199, 205 |
| Silicon Surface | 69 | Fusible | 215 |
| Silicone Surface | 59 | Gallium | 204 |
| Splice | 62 | Hard Facing | 197 |
| Spraying | 46 | Leadless Type | 197 |
| "Teflon" | 59 | Low Expansion | 197 |
| Tile | 41, 42, 43, 44 | Low Melting | 204 |
| Tin-Can Label | 61 | Low Shrinkage Aluminum | 196 |
| Tire Cord | 58 | Magnetic | 198 |
| Tube | 51 | Metal to Ceramic Bonding | 199 |
| Veneer | 58 | Neutron Absorbing | 204 |
| Vulcanizing | 49 | Pipe Bending | 204 |
| Winding | 51 | Plastic Metal | 204 |
| Wood | 58, 69 | Pyrophoric | 195, 196 |
| Wood to Aluminum | 52 | Silver | 198 |
| Adhesives | 33, 41-89 | Thermostatic | 205 |
| Aerosol Cleaner | 314, 316 | Type | 197 |
| Insecticide | 154, 157, 161, 167 | Alumina-Zirconia Solder, Metal to | 190 |
| Mothproofing | 162 | Aluminum Alloy, Low Shrinkage | 196 |
| Oven Cleaner | 316 | Bearing Alloy | 196 |
| Polish | 273, 274 | Bronze Welding Wire | 194 |
| Propellant | 168 | Cleaner | 275, 329 |
| Agricultural Fungicide | 164 | Corrosion Resistant | 186 |
| Aldrin Insecticide | 159 | Foil Adhesive | 52 |
| Alkali Metal Cleaner | 182 | Silicon Welding Flux | 191 |
| Alkyd Resin, Castor | 301 | Solder | 188 |
| Alloy, Aluminum Bearing | 196 | Soldering Flux | 190 |
| Brazing | 194 | Welding Flux | 192 |
| Film to Metal | 56 | Amber Cleaner | 317 |
| "Formica" to Wood | 52 | Ant Poison | 27 |
| for Vinyls | 45, 60, 61 | Antidim for Glass | 70 |
| Glass | 45 | Antifoam | 130, 131 |
| | | Anti-Fog for Glass | 70 |

| | | | |
|---------------------------------|----------|----------------------------------|----------------|
| Antifreeze Corrosion Inhibitors | 186 | Brushless Shaving Creams | 24 |
| Foam Inhibitor | 131 | Bubble Bath, Pine | 80 |
| Antimold Coating, Food | 141 | Buffing Composition, Antislaking | 277 |
| Antioxidant, Food | 141 | Lime | 277 |
| Antique Coloring for Copper | 29 | Buffing Compound | 283 |
| Antiseptic | 140 | Building Block, Light Weight | 178 |
| Body Powder | 117 | Bullet Tracer, Colored | 285 |
| Cord | 355 | Buying Chemicals and Apparatus | 21 |
| Ointment | 16 | | |
| Paper | 240 | Calcium Stearate | 318 |
| Rope | 355 | Calculating Costs | 21 |
| Antistatic, Wool | 343 | Canary Food | 28 |
| Apothecarie's Weight | 356 | Candles | 33 |
| Apparatus | 17 | Sootless | 287 |
| Where to Buy | 21 | Canvas, Fireproofing | 39 |
| Aquarium Cement | 34 | Car Trim Adhesive | 65 |
| Artificial Vanilla Flavor | 28 | Carbon Black, Dispersion | 137 |
| Asbestos Plaster | 180 | Electrode Binder | 67 |
| Asphalt Emulsion | 125 | Electrode Cement | 67 |
| Flameproof | 292 | Paper | 153 |
| Reducing Viscosity of | 293 | Paper Ink | 151 |
| Tile | 292 | Remover, Engine | 317, 330 |
| Atomic Numbers | 357 | Carburizer | 203 |
| Weights | 357 | Revivifying | 203 |
| Auto Polish | 31 | Carnauba Wax Emulsion | 129 |
| Avoirdupois Weight | 356 | Casein for Adhesive | 58 |
| | | Stabilized | 58 |
| Baking Powder | 27, 142 | Cattle Spray | 161 |
| Base, Perfume | 83-115 | Caulking Compound | 54, 55, 57, 68 |
| Soap Perfume | 83-115 | Cellulose Acetate Lubricant | 345 |
| Bedbug Exterminator | 27 | Screen Printing | 346 |
| Beer, Foam, Decreasing | 130 | Solvent for | 301 |
| Foam Increasing | 130 | Cement. See Adhesive. | |
| Hop Mixes | 142 | Carbon Electrode | 67, 69 |
| Binder. See Adhesive. | | Fabric Coating | 66 |
| Bitters, Hop | 142 | Film-Splicing | 69 |
| Black Shoe Polish | 31 | Floor Hardener | 33 |
| Bleach, Color Photographic | 255 | Hydraulic | 178 |
| Dry | 343 | "Neoprene" | 45 |
| Nylon | 343, 345 | Oil-Well | 66, 179 |
| Wood-Flour | 34 | Photographic Film | 69 |
| Bleaching Paper Waste | 241 | Portland | 179 |
| Wood Pulp | 244 | Quick-Setting | 179 |
| Blood Stain Remover | 336 | Removing Rust from | 314 |
| Blue-Black Finish on Steel | 29 | Self-Curing | 64 |
| Blue-Black Writing Ink | 28 | Slow-Setting | 179 |
| Body Powder, Aerosol | 117 | Spark-Plug | 62 |
| Antiseptic | 117 | Under-Water | 179 |
| Ion-Exchanger | 117 | Waterproofing | 179 |
| Boiler Compound | 40 | Centimeter | 356 |
| Corrosion Inhibitor | 188 | Ceramic Decorating Crayon | 153 |
| Bonding Metal to Ceramics | 199 | Ferromagnetic | 70 |
| Borax Weed Killer | 164 | Insulator | 71 |
| Brake Fluid, Hydraulic | 176 | Tile Grout | 72 |
| Lining | 198 | Zero Shrinkage | 71 |
| Brass, Coloring | 184 | Ceramics | 70-73 |
| Scrap Refining Flux | 192 | Cerium Etch | 184 |
| Brazing. See Welding. | | Champagne Clarifier | 142 |
| Brazing Alloy, Self-Fluxing | 194 | Chelation | 321, 322 |
| Silver | 195 | of Calcium and Magnesium | 321 |
| Brazing Flux, Titanium | 194 | of Heavy Metals | 322 |
| Brick Glaze | 71 | Chemical Specialties | 13 |
| Bright Dip, Zinc | 201 | Chemicals and Supplies, | |
| Bronze Alloy, Sliding Bearing | 196 | Sellers of | 391-405 |
| | | Where to Buy | 366-389 |

| | | | |
|-----------------------------------|------------------------|--------------------------------------|---------------|
| Chest Rubs | 26 | Tire | 318 |
| Chewing Gum Base | 302 | Toilet Bowl | 328 |
| Chimney Soot Cleaner | 318 | Upholstery | 313 |
| Chipboard to Aluminum Adhesive .. | 52 | Wall | 333, 342 |
| Chlordane Emulsion | 157 | Watch Parts | 329 |
| Insecticide | 157 | Waterless Hand | 319 |
| Chromium Plate, Stripping | 211 | White Wall Tire | 318 |
| Circular Measure | 356 | Woodwork | 315 |
| Citrus Fungicide | 164 | Cleaners and Soaps | 35 |
| Clarification and Filtering | 19 | Cleanser. See Cleaner. | |
| Cleaner. Also see Detergent, | | Cleansing Cream, Neutral | 16 |
| Remover, Soap. | | Cleansing Creams | 22 |
| Aerosol | 313, 314 | Cloth Adhesive | 41, 45 |
| Aerosol Oven | 316 | Clothing Insecticide | 154 |
| All-Purpose | 341 | Coating. Also see Lacquer, | |
| Aluminum | 275, 329, 332 | Paint, Varnish. | |
| Amber | 317 | Awning | 302 |
| Auto | 272, 274 | for Metals | 181 |
| Baking Pan | 329 | for Paper | 239, 245-253 |
| Brake-Lining | 330 | Rustproofing | 188 |
| Brass | 332 | Cocoa-Malt Powder | 28 |
| Building Maintenance | 327 | Coffee, Instant Tablet | 142 |
| Ceramic | 328, 332 | Cold Creams | 22 |
| Chimney Soot | 318 | Color Developer Accelerator | 344 |
| Clear Emulsion | 331 | Coloring Brass | 184 |
| Copper | 332 | Copper | 184 |
| Diode Assembly | 315 | Titanium | 185 |
| Drain | 315 | Compost Fertilizer | 139 |
| Driveway | 332 | Compounding | 13 |
| Dry | 312 | Containers for | 17 |
| Electrical Insulator | 331 | Concrete Shrinkage, Decreasing .. | 179 |
| Engine | 330 | Consulting Service | 21 |
| Eyeglass | 314 | Containers for Compounding | 17 |
| Floor | 333, 342 | Copper Brazing Alloy | 194 |
| Fossil | 317 | Casting Alloy | 196 |
| Fur | 170 | Coloring | 184 |
| Furniture | 331 | Coloring, Antique | 29 |
| Germicidal | 309 | Cord, Antiseptic | 355 |
| Granite | 326 | Rat Repellent for | 164 |
| Hand | 320 | Ratproof | 344 |
| Hard Surface | 315 | Core Adhesive, Paper | 51 |
| Hardwood Floor | 315 | Binder, Foundry | 202 |
| Household | 326 | Winding | 51 |
| Industrial Hand | 320 | Cork Binder | 67 |
| Laboratory Glass | 314 | Corrosion Inhibiting Paper | 240 |
| Marble | 326 | Corrosion Inhibitor, Boiler Water .. | 188 |
| Metal | 181-183, 275, 328, 332 | Fuel Gas Tanks | 187 |
| Metal Parts | 315 | Gun Barrel | 188 |
| Old Painting | 318 | Volatile | 185, 186, 187 |
| Oven | 316 | Well Pipes | 187 |
| Paint | 315 | Corrosion Proofing Emulsion | 125 |
| Paint Brush | 333 | Magnesium | 186 |
| Plastic | 331 | Razor Blades | 187 |
| Polystyrene | 331 | Rubber-Metal Parts | 187 |
| Porcelain | 328 | Tin | 186 |
| Printers' | 328 | Zinc | 186 |
| Printing Press | 328 | Corrosion Resistant Coating | 186 |
| Radiator | 316 | Corrosive Chemicals | 20 |
| Reflector | 313 | Cosmetic Emulsions | 124 |
| Rug | 337 | Perfumes | 85-117 |
| Safety Glass | 314 | Cosmetics | 74-123 |
| Sanitizing | 308 | Costing Calculation, Typical | 21 |
| Silver | 200, 275, 329 | Costs | 21 |
| Spark Plug | 328 | Crayon | 287 |
| Tile | 332, 333 | Ceramic Decorating | 153 |

| | | | |
|---|---------------|-------------------------------------|-------------------------|
| Green Marking | 29 | Calcium Carbonate | 136 |
| Cream, Aftershave | 83 | Calcium Silicate | 136 |
| Shampoos | 76, 77 | Carbon Black | 137 |
| Cresol Disinfectant | 27 | Casein (Stable) | 136 |
| Crucible Glaze, Graphite | 71 | Clay | 136 |
| Crystal Cement | 61 | Colloidal Clay | 136 |
| Crystal Growth in Canned Goods, Preventing | 144 | Kaolin | 136 |
| Cuticle Remover | 80 | Phenyl-2-naphthylamine | 136 |
| | | Potassium Cresylate | 136 |
| | | Sulfur | 137 |
| "Dacron", Dyeing | 349 | Titanium Dioxide | 137 |
| Sizing | 354 | Dissolving and Mixing | 19 |
| Solvent for | 302 | Documents, Reconditioning | 240 |
| Dangerous Chemicals | 20 | Dog Repellent | 140, 163 |
| DDT Insecticides | 160 | Drain Cleaner | 315 |
| Decalcomania, Bleedproof | 302 | Drawing Lubricants | 173 |
| Decolorizing | 19 | Drilling Emulsion, Oil-Well | 125 |
| Decontaminating Air | 316 | Drugs | 118 |
| Walls | 316 | Dry Cleaner | 312 |
| Defoamers | 130, 131 | Dry-Cleaning Fluid | 35 |
| Defoliant, Cotton | 139 | Dry Fire Extinguisher | 39 |
| Plant | 164 | Dry Measure | 356 |
| Deinking Newsprint | 318 | Duplicating Fluid | 147 |
| Paper | 241 | Paper | 238 |
| Waste Paper | 238 | Dust Filter Adhesive | 57 |
| Dental Alloy | 197 | Dye. Also see Color. | |
| Silver Solder Flux | 194 | "Algol" | 351 |
| Deodorant, Foot | 117 | "Celliton" | 350 |
| Spray | 26 | Chrome | 350 |
| Deoxidizing Iron and Steel | 183 | Dye Emulsion, Aniline Black | 345 |
| Desizer, Heat-Stable Enzyme | 344 | Flash Aging | 345 |
| Desizing Glass Cloth | 353 | Dye Paste Thickener | 344 |
| Detergent, Aerosol | 313 | Dye, Vat | 350 |
| Automatic Washer | 311 | Dyeing "Acrilan" | 348 |
| Bleach | 310 | "Dacron" | 349 |
| Controlled Suds | 325 | "Dynel" | 347 |
| Dishpan | 312 | "Orlon" | 346 |
| Dishwashing | 310, 324 | Synthetic Fibers | 346 |
| Germicidal Dishwasher | 325 | "Dynel", Dyeing | 347 |
| Heavy-Duty | 310 | | |
| High Foam | 311 | Editors, Board of | 5 |
| Hosiery | 312 | Electric Contact Amalgam | 199 |
| Laundry | 311, 338, 339 | Electric Fuse Alloy | 199 |
| Liquid | 310, 326 | Resistance Alloy | 199 |
| Low-Foaming | 311 | Resistance Wire | 205 |
| Low Temperature | 310 | Electrical Apparatus, Lubricant for | 174 |
| Machine Dishwasher | 325 | Fuse Alloy | 205 |
| Machine Dishwashing | 308 | Resistance Alloy | 197 |
| Metal | 332 | Electrocleaner | 208 |
| Paper Deinking | 241 | Electrode Binder, Carbon | 67, 69 |
| Salt-Water | 311 | Electroplating. See Plating. | |
| Sanitizer | 310, 327 | Electropolishing | 200, 211 |
| Soap Bar | 318 | Zirconium | 201 |
| Soapless Bar | 327 | Elements, Chemical | 357 |
| Stable-Foam | 332 | Emulsion, Adhesive | 47, 52, 53 |
| Synthetic Bar | 327 | Aldrin | 159 |
| Detonator Delay | 284 | Allyl Starch | 127 |
| Developers, Photographic | 254, 255 | Aniline Black | 345 |
| Developing Solution | 40 | Anionic | 259 |
| Die Alloy, Forming | 197 | "Armowax" | 129 |
| "Dieldrin" Insecticide | 158 | Asphalt | 125 |
| Dielectric | 291 | Carnauba | 263 |
| Adhesive | 58 | Carnauba Wax | 129 |
| Ceramic | 71 | Cationic | 125, 129, 169, 170, 261 |
| Dispersion, Antimony Oxide | 137 | Chlordane | 157 |

| | | | |
|-------------------------|------------------|---------------------------------------|----------|
| Clear | 331 | Fabric to Aluminum Adhesive | 52 |
| Cosmetic | 124 | Fabrics, Fireproofing | 344 |
| DDT | 160 | Fireproofing Light | 39 |
| "Dieldrin" | 158 | Face Lotion, Vinegar | 17 |
| Diocetyl Phthalate | 292 | Fast-Drying Adhesives | 46 |
| Drying Oil | 125 | Fat Liquoring | 169, 170 |
| "Endrin" | 158 | Ferromagnet | 198 |
| Fat-Liquor | 169 | Ceramic | 70 |
| Flash Aging | 345 | Fertilizer, Peat | 138 |
| Floor Waxes | 268-273, 279-282 | Fiber. Also see Textile. | |
| Hydrogen Peroxide | 126 | Adhesive | 56 |
| Insecticide | 155 | Fiberboard, Proofing | 37, 38 |
| Lemon Oil | 131 | Figuring | 15 |
| Lime Oil | 132 | Filtering and Clarification | 19 |
| Lindane | 155 | Fire Extinguisher | 39 |
| Low-Viscosity Wax | 132 | Kindler | 39 |
| Metal Cleaner | 328 | Fireproof Paper | 39 |
| Metal Cleaning | 182 | Fireproofing. Also see Flameproofing. | |
| Methyl Parathion | 155 | Canvas | 39 |
| Mineral Oil | 273 | Jute | 344 |
| Nonionic | 129, 169, 260 | Light Fabrics | 39 |
| Nonionic Wax | 128 | Fishnets, Rotproofing | 352 |
| Nylon | 127 | Flameproofing. Also see Fireproofing | |
| Oil | 160 | Textiles | 344 |
| Oil-in-Water | 118 | Flange Lubricant | 174 |
| Oil-Well Drilling | 125 | Flare, Signal | 284 |
| Paint | 221 | Flat Paint | 224 |
| Paraffin Wax | 128 | Flavor, Artificial Vanilla | 28 |
| Polish | 258-282 | Emulsions | 131, 132 |
| Polyethylene | 258-265 | Intensifier, Food | 141 |
| Resin | 261 | Mushroom | 141 |
| Ringless Orange | 131 | Flexible Glue | 16 |
| Rustproofing | 187 | Floor Cleaner, Hardwood | 315 |
| Silicone | 127, 153 | Oil | 32 |
| Spraying Oil | 160 | Oil Absorbent | 327 |
| Tar | 125 | Wax | 31 |
| "Teflon" | 127 | Flooring Organosol | 306 |
| Textile Printing | 344 | Flower Preservative, Cut | 138 |
| "Thiokol" | 135 | Flux. See also Soldering Flux. | |
| "Toxaphene" | 157 | Ceramic Welding | 192 |
| Transparent Oil | 126 | Galvanizing | 192 |
| Turbine Oil | 125 | Liquid Soldering | 192 |
| "Vistanex" | 127 | Soldering | 192 |
| Water-in-Oil | 124 | Solvent | 317 |
| Waterproofing | 128 | Fly Paper | 27 |
| Emulsions | 124-135, 258-282 | Spray | 26, 161 |
| Enamel, Paint | 235 | Spray, Cattle | 161 |
| "Endrin" Insecticide | 158 | Foam, Beer | 130 |
| Engine Cleaner | 330 | Control | 252 |
| Degreaser | 316 | Inhibitors | 130, 131 |
| Enzyme Desizer | 344 | Foamed Plastic | 305 |
| Etch, Cellulose Acetate | 301 | Urethane | 287 |
| Cerium | 184 | Foliage Preservative | 138 |
| Metal | 184 | Food Products | 141-145 |
| Etching Fluid for Glass | 30 | Foot Powder, Deodorant | 117 |
| Germanium | 184 | Powders | 25 |
| Magnesium | 184 | Formulation | 13, 14 |
| Steel | 184 | Fossil Cleaner | 317 |
| Zinc | 184 | Foundry Core Binder | 202 |
| Eutectics, Alloy | 215 | Core Mix | 212 |
| Experimenting | 15 | Core Wash | 202, 203 |
| Explosive, Blasting | 284 | Mold Coating | 70 |
| Exterior Paints | 225-235 | Molding Sand | 201 |
| Extract, Pure Lemon | 28 | Friction Alloy, Powdered Metal | 198 |
| Extrusion Lubricants | 173 | Tape | 294 |

| | | | |
|---------------------------|---------------|---------------------------------|----------|
| Fruit Peeling Liquid | 138 | Gun Barrel Corrosion Inhibitor | 188 |
| Fumigant | 154, 162, 163 | Gypsum Mold, Porous | 201 |
| Grain | 163 | | |
| Nonflammable | 163 | Hair Coloring | 79 |
| Peanut Storage | 162 | Removal, Hide | 169 |
| Fungicide, Agricultural | 164 | Rinse | 77, 79 |
| Citrus | 164 | Shampoo | 76 |
| Grape-Vine | 168 | Wave Neutralizer | 74 |
| Oak Wilt | 164 | Wave, Odorless | 74 |
| Rope | 164 | Wave, Paste | 74 |
| Fur Cleaning | 170 | Hand-Lotions | 23, 24 |
| Glazing | 170 | Heat Insulation | 178 |
| Skin Softener | 170 | Transfer Fluid | 177 |
| Furnace Lining | 178 | Heating | 17 |
| Furniture Polish | 32 | Hectograph Ink | 147 |
| Furs | 169 | Solvent | 147 |
| Fusible Alloys | 215 | Transfer Sheet | 146 |
| | | Henna, White | 80 |
| Gallium Alloy | 204 | Herbarium Insecticide | 167 |
| Galvanized Wire Lubricant | 173 | Hide, Dehairing | 169 |
| Galvanizing, Electrolytic | 199 | Softener | 169, 170 |
| Flux | 192 | Wool Removal from | 169 |
| Gasket, Refrigerator | 289 | High-Temperature | |
| Gasoline, Solidified | 39 | Electric Resistance Alloy | 199 |
| Germanium Etch | 184 | Hop Bitters | 142 |
| Germicide. See Sanitizer. | | Horse-Radish Preservative | 141 |
| Gibberellin Aerosol | 139 | Hosiery Scour | 312 |
| Glass Adhesive | 45, 52 | House Paints | 224, 226 |
| Anti-Fog for | 70 | Household Cleaner | 36 |
| Cleaner | 314 | Hydraulic Brake Fluid | 176 |
| Cloth, Desizing | 353 | Shock Absorber Fluid | 177 |
| Etching Fluid | 30 | Hydrogen Peroxide Emulsion | 126 |
| Fiber Adhesive | 57 | | |
| Joint Mastic | 61 | Incense | 154 |
| Marking Ink | 15 | Indelible Laundry Ink | 29 |
| Glassine Paper | 37 | Ingredients | 14 |
| Glaze, Brick | 71 | Inhibitor, Antifreeze Corrosion | 186 |
| Glazes | 71 | Corrosion | 176 |
| Glazing, Fur | 170, 171 | Pickling | 183 |
| Gloss Paint | 223 | Volatile Corrosion | 185 |
| Glue, Flexible | 16 | Ink, Ball Point Pen | 147 |
| Grafting Wax | 32 | Blue-Black Writing | 28 |
| Grain Fumigant | 163 | Carbon Paper | 151 |
| Gram | 356 | Drawing | 147 |
| Granite Cleaner | 326 | Duplicating | 146 |
| Grape-Vine Fungicide | 168 | Flexographic | 149 |
| Graphite, Colloidal | 175 | Fluorescent | 149 |
| Crucible Glaze | 71 | for Marking Glass | 15 |
| Electrode Binder | 67 | Gelatin Printing | 149 |
| Grease | 32 | Heat-Set | 150 |
| Lubricant | 175 | Indelible Laundry | 29 |
| Mold Coating | 70 | Laundry Marking | 147 |
| Solder for | 189 | Letterpress | 148 |
| Grease, Cutting Compound | 314 | Litho | 148 |
| Lubricating | 175, 176 | Marking | 147 |
| Remover, Engine | 316 | Nonmisting Printing | 150 |
| Resistant Paper | 237 | Offset | 148 |
| Greaseproofing Paper and | | Photographic Film Marking | 147 |
| Fiberboard | 38 | Printing | 148 |
| Green Marking Crayon | 29 | Rotary Press | 149 |
| Grinding and Pulverizing | 20 | Screen | 149 |
| Grout, Ceramic Tile | 72 | Stain Remover | 334 |
| Gum Base, Chewing | 302 | Stencil | 146 |
| Lubricants | 32 | Tin Printing | 148 |
| | | Typewriter Ribbon | 147 |

- Vapor Set 150
 Water-Base Printing 151
 White Cellophane 148
 Insect Repellent 26, 154, 166
 Insecticide. Also see Spray.
 Aerosol 154
 Agricultural 158-162
 Aldrin 159
 Clothing 154
 Cotton 165
 DDT 160
 "Dieldrin" 158
 "Endrin" 158
 Phosdrin 158
 Self-Vaporizing 167
 "Strobane" 156
 Thermal 167
 Wettable Powder 155
 Insulating Tape, Electrical 294
 Insulation, Building Wire 298
 Electric Wire 300
 Heat 178
 Plastic 291
 Thermal 178
 Insulator, Ceramic 71
 Interior Paints 225-235
 Investment Binder 213
 Iron, Deoxidizing 183
 Hardener 203
 Scale Remover 182
 Soldering Flux 193
 Stain Removal 322
 Zinc Coating 181
 Javelle Water 37
 Jewelers' Casting Sand Binder 201
 Kilogram 356
 Kilometer 356
 Knitting-Needle Oil 174
 Label Adhesive 61
 Lacquer 217
 Laminating Adhesive 56
 Fibers 56
 Larvicide 160
 Latex Backing 291
 Mold Release Lubricant 175
 Paint 229
 Laundry Blue, Liquid 37
 Detergent 338, 339
 Ink 147
 Ink, Indelible 29
 Stains, Preventing 321
 Lead Coating Metals 181
 Extrusion Lubricant 173
 Leather 169
 Pasting 170
 Preservative 30
 Softeners 169, 170
 to Cloth Adhesive 41, 45
 to Paper Adhesive 41, 45
 Lighter Flint Alloy 195
 Lindane Emulsion 155
 Liniments 25, 26
 Lipstick Stain Remover 318
 Liquefying Cleansing Cream 22
 Liquid Laundry Blue 37
 Measure 356
 Polishing Wax 32
 Soap Concentrate 35
 Liter 356
 Long Measure 356
 Loss and Spoilage 20
 Low-Resistance
 Electrical Fuse Alloy 205
 Lubricant. Also see Drawing Oil,
 Grease, Oil.
 Aerosol 175
 Cellulose Acetate 345
 Drawing 173
 Dry Film 175
 Electrical Apparatus 174
 Extreme Pressure 174, 175
 Flange 174
 Graphite 175
 Grease 175, 176
 Gum 32
 Latex Mold Release 175
 Lead 173
 Lead Extrusion 173
 Molding 175
 Needle 174
 Plastic Molding 175
 Plug Valve 174
 Pressure 174, 175
 Release 175
 Removing Silicone 314
 Stable Grease 175, 176
 Synthetic 174
 Textile 174, 343
 Valve Spindle 174
 Wire Drawing 173
 Wool 343
 Yarn 345
 Magnesium, Corrosion Proofing 186
 Etch 184
 Melting Flux 193
 Solder 189
 Soldering Flux 193
 Zirconium Welding Flux 193
 Magnet, Ferro 198
 Permanent 198
 Magnetic Compensating Alloy 198
 Malted-Milk Powder 28
 Marble Cleaner 326
 Marking Ink, Glass 15
 Mastic. See Adhesive.
 Glass Joint 61
 Measuring and Weighing 20
 Meat Color Preservative 141
 Fast Curing 145
 Tenderizer 142
 Mechanics' Hand-Soap Paste 35
 Mercerizing Penetrant 344
 Meringue, Swiss 144
 Metal Abrasive 283
 Casting Mold 211
 Cleaner 181, 182, 183, 275, 315, 332

| | | | |
|--------------------------------|------------|----------------------------------|-------------------------|
| Coloring | 184, 185 | Soluble | 172, 174 |
| Cutting Oil | 172 | Water Dispersible | 173 |
| Defect Detector | 203 | Oil-Well Cement | 66, 179 |
| Dips | 200, 201 | Drilling Mud Additive | 177 |
| Drawing Compound | 173 | Oilproofing Paper and Fiberboard | 38 |
| Etching | 184 | Oils, Solubilizing Flavor | 126 |
| Lead Coating | 181 | Ointment, Antipruritic | 123 |
| Polish | 30, 274 | Antiseptic | 16 |
| Reflectivity of | 206 | Base, Washable | 118 |
| Sintered | 198 | Bases | 118-122 |
| Sinters | 198, 199 | Cod-Liver Oil | 122 |
| Stop-Off | 211 | Glyceryl | 123 |
| to Cloth Adhesive | 41, 45, 52 | Wound | 122 |
| to Paper Adhesive | 41, 45, 52 | Optical Cement | 61 |
| Meter | 356 | Orange Oil Emulsion, Ringless | 131 |
| Methods | 17 | Ore Pellet Binder | 204 |
| Metric Equivalents | 356 | Organosol, Awning Coating | 302 |
| Mildewproofing, Textile | 351 | Dipping | 306 |
| Mixing and Dissolving | 19 | "Orlon", Dyeing | 346 |
| Mold, Casting Shell | 201 | Sizing | 354 |
| Facing, Foundry | 202, 203 | Oven Cleaner | 316 |
| Filler, Foundry | 203 | Paint | 217 |
| Foundry | 202, 203 | Alkyd | 221, 233 |
| Metal Casting | 211 | Brush Cleaner | 36 |
| Porous Gypsum | 201 | Chlorinated Rubber | 233 |
| Release, Cast Steel | 204 | Cleaner | 315 |
| Molding Compound | 32, 293 | Eggshell | 221 |
| Sand, Foundry | 201 | Emulsion | 221, 225, 226, 227, 230 |
| Moldproofing Food | 141 | Flat | 224 |
| Mortar, Cement | 179 | Gloss | 223 |
| Sand, Prepared | 179 | House | 224 |
| Mosquito-Repelling Oil | 26 | Latex | 229 |
| Mothproofing | 351 | Latex-Alkyd | 227 |
| Aerosol | 162 | Lead-Free | 224 |
| Fluid, Nonstaining | 27 | Limed Wall | 224 |
| Mouth Washes | 24, 25 | Odorless | 234 |
| Neoprene Compound | 299 | Outside White | 226 |
| Neutral Cleansing Cream | 16 | Polyvinyl Acetate | 225, 227, 230 |
| Neutron Absorbing Alloy | 204 | Primer | 217-220 |
| Newspaper Recovering | 241, 318 | Remover | 34, 333 |
| Newsprint, Deinking | 318 | Semi-Gloss | 221 |
| Nickel, Brightening | 211 | Stipple | 233 |
| Plating, Bright | 199, 200 | Texture | 232 |
| Welding Flux | 193 | Thickener | 228 |
| Nicotine Reduction, Tobacco | 139 | Thixotropic | 234 |
| Stain Remover | 319 | Trim | 223 |
| Noncorrosive Soldering Flux | 40 | Water Base | 225 |
| Nonskid for Oily Rails | 177 | White Wall | 226 |
| Nonstaining Mothproofing Fluid | 27 | Paintings, Cleaning Old | 318 |
| Nylon Adhesive | 65 | Palladium Plating | 210 |
| Bleach | 343 | Paper | 237 |
| Bleaching | 345 | Antiseptic | 240 |
| Dispersion | 127 | Black Cover | 239 |
| Whitening | 345 | Bleaching Waste | 241 |
| Oak Wilt Fungicide | 164 | Carbon | 153 |
| Odor Improvement of Resins | 302 | Coatings | 238-253 |
| Odors, Perfuming | 83-115 | Coating, Wax | 237 |
| Oil, Cutting | 172 | Colored | 245 |
| Knitting-Needle | 174 | Corrosion Inhibiting | 240 |
| Lubricating | 173-175 | Deinking | 238, 241, 318 |
| Rustproofing | 173 | Electrolytic Recording | 244 |
| Slushing | 187 | Facsimile Recording | 240 |
| | | Fireproof | 39 |
| | | Greaseproof | 239, 246, 250 |

| | | | |
|--------------------------------|----------|----------------------------------|-------------------|
| Grease Resistant | 237 | Fire-Retardant | 307 |
| High-Finish Book | 245 | Flooring | 288 |
| Metallic Decorated | 239 | Foamed | 305 |
| Proofing | 37, 38 | Garden Hose | 289 |
| Red Coating for | 245 | Insulation | 291 |
| Size for Photograph | 246 | Lens, Antifogging for | 301 |
| Stiff Match | 246 | Metal Alloy | 204 |
| Stiff Saturated | 243 | Mothkilling | 301 |
| Telegraphic Facsimile | 238 | Opaque | 291 |
| to Metal, Adhesive | 45 | Stabilizer | 307 |
| Translucent Duplicating | 238 | Temperature Resistant | 301 |
| Transparentizing Bond | 238 | Wood | 34 |
| Transparent Waterproof | 240 | Plastics Adhesive | 59, 61 |
| Vapor Proof | 239 | Plasticizer | 290 |
| Vegetable Parchment | 238 | Polyethylene | 293 |
| Very White | 244 | Plastisol, Vinyl | 305 |
| Waterproof | 239 | Plating | 199, 200, 207-211 |
| Paperhanger's Paste | 33 | Brush | 200 |
| Paraffin Wax Emulsion | 128 | Nickel | 199, 200 |
| Wax Improvers | 286 | Palladium | 210 |
| Parathion Insecticide Methyl | 155 | Platinum | 209 |
| Paste. See Adhesive. | | Rhodium | 205-209 |
| Auto and Floor Wax | 31 | Silver | 200 |
| Soap | 35 | Platinum Plating | 209 |
| Wallpaper | 58 | Pointing Compound, Tile | 73 |
| Patina on Brass | 184 | Poison, Ant | 27 |
| on Copper | 184 | Poisonous Metals, Removing | 183 |
| Paving Composition, Cold | 180 | Poisons | 20 |
| Peanut Storage Fumigant | 162 | Polish | 31, 258-283 |
| Peat Fertilizer | 138 | Aerosol | 273 |
| Pen Points, Non-Corroding | 197 | Aluminum | 275 |
| Penetrating Oil | 32 | Automobile | 266, 272 |
| Perfume Base | 83-115 | Ball Bearing | 274 |
| Base, Soap | 83-115 | Bright Drying | 258-272 |
| Stick | 115-117 | Chemical Steel | 275 |
| Water-Soluble | 117 | Cleaner | 274 |
| Petroleum Resin Deodorizer | 302 | Floor | 258-272 |
| Phenolic Moldings, Glazing | 294 | Furniture | 265 |
| Recovering Inserts from | 293 | Insecticide Floor | 277 |
| Phosdrin Insecticide | 158 | Leveling Agent for | 264 |
| Phosphating Steel | 181 | Liquid Wax | 269 |
| Photographic Bleach, Color | 255 | Metal | 274 |
| Developer | 254, 255 | Non-Rubbing | 258-272 |
| Film, Recondition Exposed | 256 | Oil | 273 |
| Film, Stayflat | 256 | Paste | 272, 276 |
| Solutions | 40 | Shoe | 282 |
| Wash | 254 | Silicone Cloth | 273 |
| Pickling Inhibitor | 183 | Silver | 276 |
| Liquor, Recovering | 183 | Solvent-Wax | 283, 284 |
| Titanium-Zirconium | 183 | Steel | 275 |
| Pipe Bending Alloy | 204 | Waxless | 274 |
| Pitch Formation, Preventing | 244 | Wax Paste | 265-282 |
| Plant Defoliant | 164 | Polishing. See Electropolishing. | |
| Plaster, Asbestos | 180 | Wax Liquid | 32 |
| Colored | 180 | Polyethylene Adhesive | 57 |
| High-Expansion | 180 | Emulsion | 258-265 |
| Interior | 180 | Non-Cracking | 301 |
| Wall-Patching | 33 | Plasticizer | 293 |
| Plastic | 287-307 | Polystyrene Adhesive | 57 |
| Antiseptic | 305 | Polyurethane, Foamed | 287 |
| Cleaner for | 331 | Polyvinyl Chloride Sheet | 288, 303 |
| Expanded. See Plastic, Foamed. | | Porcelain Repair Coating | 71 |
| Extruding | 306 | Potato Sprouting Stimulant | 139 |
| Film, Blown | 289 | Powder, Baking | 27 |
| Film, Unsupported | 303, 305 | Cocoa-Malt | 28 |

| | | | |
|--------------------------------|----------|-----------------------------------|--------------------|
| Malted Milk | 28 | Resins | 286 |
| Sweet Cocoa | 28 | Resistance Wire | 205 |
| Precision Casting Mix | 213 | Rhodium Plating | 205-209 |
| Preparations, Elementary | 22 | Rimming Agent, Steel | 203 |
| Preservative, Rubber | 293 | Rodenticide | 163 |
| Preservatives for Food | 141 | Rope, Antiseptic | 355 |
| Primer, Alkyd | 217 | Preservative | 164 |
| Anti-Corrosive | 217 | Rosin Size, Stable | 246 |
| Concrete Floor | 217 | Rotproofing Fishnets | 352 |
| Etching | 218 | Rubber | 286 |
| Maritime | 217 | Compounds | 295-299 |
| Wash | 218-220 | Preservative | 293 |
| Printing Inks | 148-151 | Rug Cleaner | 337 |
| Projectile, Igniter for | 284 | Shampoo | 312, 313 |
| Tracer | 285 | Rust and Ink Remover | 36 |
| Pulverizing and Grinding | 20 | Prevention Compound | 30 |
| Pure Lemon Extract | 28 | Remover | 182, 314, 329 |
| Putty | 34 | Rustproofing Coating | 188 |
| Glass | 58 | Compounds | 185-188 |
| Metal | 58 | Emulsion | 187 |
| Wood | 58 | Oil | 173 |
| Pyrophoric Alloy | 195 | Sacks, Rat Repellent for | 164 |
| Pyrotechnics | 284 | Saddle Soap | 35 |
| Pyroxylin Film, Noninflammable | 293 | Salt, Noncaking | 142 |
| Substitute | | Substitute | 142 |
| Quartz to Metal Solder | 190 | Saltless Curing | 145 |
| Rabbit Skin Cure | 170 | Sanitizer, Quaternary | 308 |
| Radiator Cleaner | 316 | Scale Removers | 182, 183 |
| Radiographic Contrast Agent | 256 | Scouring Powder, Home | 342 |
| Rat Repellent | 164 | Screen Printing Emulsion | 346 |
| Ratproof Cordage | 344 | Seal. See also Adhesive. | |
| Rayon Cord Dip | 351 | Ammonia Resistant | 66 |
| Razor Blade Corrosion Proofing | 187 | Sealant. See Adhesive. | |
| Strop Compound | 277 | Seed Protection Against Crows | 139 |
| Reflectivity of Metals | 208 | Sellers of Chemicals and Supplies | 391 |
| Reflector Cleaner | 313 | Semiconductor, Soldering | 189 |
| Refractory | 178 | Sewage Defoamer | 130 |
| Coating | 70 | Shampoo, Hair | 76 |
| Mix, Precision Casting | 213, 214 | Rug | 312, 313, 337, 338 |
| Remover, Blood Stain | 336 | Shave Cream, Aerosol | 81 |
| Calcium Salt | 317 | Cream, Brushless | 24, 82 |
| Carbon | 330 | Lotion, pre- | 80 |
| Engine Carbon | 317 | Shaving Soap | 341 |
| Finger-Print | 331 | Shellac Dispersion | 278 |
| Floor Wax | 327 | Solution | 263 |
| Grease | 314 | Shock Absorber Fluid | 177 |
| Ink Stain | 334 | Shoe Adhesive | 49 |
| Iron Stain | 322 | Dressing, White | 30 |
| Lipstick Stain | 318, 334 | Polish | 282 |
| Nicotine Stain | 319 | Polish, Black | 31 |
| Paint | 333 | Shortening, Cake | 144 |
| Rust | 314, 329 | Liquid | 144 |
| Silicone Grease | 314 | Signal Flare | 284 |
| Silicone Resin | 331 | Silicate Adhesive | 61 |
| Sink Stain | 328 | Silicon-Aluminum Welding Flux | 191 |
| Tar | 333 | Silicone Emulsion | 127, 154 |
| Tarnish | 329 | Grease Remover | 314 |
| Tobacco Stain | 337 | Polish | 265 |
| Water Soluble Stain | 336 | Polishing Cloth | 273 |
| Repellent, Dog | 140 | Resin Remover | 331 |
| Insect | 166 | Silver Alloy, Corrosion Resistant | 205 |
| Resin, Alkyd | 302 | Brazing Alloy | 195 |
| Emulsion | 261 | Brightener | 200 |
| Odor Improvement of | 302 | Cleaner | 275, 329 |

- Dip 200, 276, 329
 Nontarnishing 198, 205
 Plating 200
 Polish 276
 Removing Iron Stain from 184
 Solder 189
 Soldering Flux 194
 Size, "Acrilan" 354
 Acrylic Yarn 354
 "Dacron" 354
 High Wet-Strength Paper 246
 "Orlon" 354
 Paper 246, 248
 Photographic Paper 246
 Rosin 246
 Sizing. See Size.
 Skin, Animal. See Hide.
 Slushing Oil 187
 Smoke, Pyrotechnic 285
 Soap, Coconut Oil 340, 341
 Metallic 318
 Perfume 83-115
 Salt-Water 340
 Scrub 342
 Shaving 341
 Transparent 340
 Soaps 308
 and Cleaners 35
 Softener, Textile 343
 Water 323
 Solder, 300°C. 189
 All-Metals 189
 Alumina-Zirconia to Metal 190
 Aluminum 188
 Graphite 189
 Hard 188
 Magnesium 189
 Non-Ferrous Alloy 188
 Quartz to Metal 190
 Semi-Conductor to Leads 189
 Silver 189
 Stainless Steel 189
 Steel 188
 Soldering Flux 40, 190
 Aluminum 190
 Dental 194
 Hard 191
 Iron 193
 Light Metal 193
 Magnesium 193
 Residueless 191
 Welding 191
 Solidified Gasoline 39
 Solubilizing Flavor Oils 126
 Soluble Oils 172, 174
 Solvent, Soldering Flux 317
 Soot Cleaner, Chimney 318
 Sore-Muscle Liniment 26
 Sorel Cement, Waterproofing 179
 Spark Plug Cement 62
 Spindle Lubricant 174
 Spoilage and Loss 20
 Spot Removal 335
 Remover 36
 Spray, Cattle 161
 Fly 161
 Insecticide 161
 Tobacco 168
 Square Measure 356
 Stain. See also Remover.
 Stain Remover, Blood 336
 Remover, Ink 334, 335
 Remover, Lipstick 318, 334
 Remover, Nicotine 319
 Remover, Water-Soluble 336
 Removing from Cotton 322
 Spotting 335
 Stainless Steel, Electropolishing 211
 Stains on Silver, Removing 184
 Preventing Laundry 321
 Starch Binder, Removing 353
 Corrugating 49
 Emulsion 127
 Gloss 343
 "Soluble" 353
 Thin-Boiling 354
 Steel, Blue-Black Finish for 29
 Corrosion Inhibitor for 186
 Deoxidizing 183
 Drawing Compound 173
 Etch 184
 Hardener 203
 Phosphatizing 181
 Pickling Liquor, Recovering 183
 Quenching Bath 203
 Rimming Agent 203
 Solder 190
 Soldering Stainless 189
 Welding Flux 192
 Sticker, Agricultural Spray 161
 Straw-Hat Cleaner 36
 Strawboard Coating 244
 Strobane Insecticide 154
 Styptic Stick 118
 Sugar-Refining Antifoam 130
 Sulfur Dispersion 137
 Supplies and Chemicals,
 Sellers of 391-405
 Where to Buy 366-405
 Sweet Cocoa Powder 28
 Symbols for Elements 357
 Syndet Soap Bar 318
 Synthetic Fibers, Dyeing 346
 Tantalum, Electropolishing 200
 Tar Emulsion 125
 Remover 333
 Technical Magazines 21
 "Teflon" Emulsion 127
 Temperature Measurement 18
 Tenderizer, Meat 142
 "Terylene". See Dacron.
 Textile, Antiseptic 352
 Flameproofing 344
 Mercerizer Aid 344
 Mildewproofing 351
 Mothproofing 351
 Printing Emulsion 344
 Printing Paste Extender 344

| | | | |
|-------------------------------------|------------|----------------------------------|----------|
| Printing, Spray | 345 | Waste Paper, Recovering | 241, 318 |
| Softener | 343 | Water Glass. See Silicate. | |
| Thermal Insulation | 178 | Repellent, Dry Cleaners' | 336 |
| Thermostatic Alloy | 205 | Softening | 323 |
| "Thiokol" Emulsion | 135 | Waterproofing Cement | 38 |
| Tile Adhesive | 41-44 | Emulsion | 128 |
| Asphalt | 292 | for Shoes | 30 |
| Cleaner | 332, 333 | Heavy Canvas | 38 |
| Pointing Compound | 73 | Liquid | 38 |
| Synthetic Rubber | 297 | Paper and Fiberboard | 37 |
| Tin, Corrosion Proofing | 186 | Wax, Antioxidant | 286 |
| Tinning, Dry | 181 | Defoamer for | 286 |
| Tint Base, Paint | 229 | Emulsion, Low Viscosity | 132 |
| Tire Cleaner | 318 | Emulsion, Paraffin | 128 |
| Cord Dip, Rayon | 351 | Mold Coating, Refractory | 287 |
| Titanium, Blackening | 185 | Non-Blocking | 286 |
| Brazing Flux | 194 | Polish | 263-282 |
| Dioxide Dispersion | 137 | Powdered | 286 |
| Electropolishing | 200 | Remover | 327, 332 |
| Extrusion Lubricant | 173 | Sealing | 286 |
| Zirconium, Pickling | 183 | Weed Killer. See Also Herbicide. | 164 |
| Tobacco Nicotine Reduction | 139 | Weighing and Measuring | 20 |
| Spray | 168 | Weights and Measures | 356 |
| Stain Remover | 337 | Welding | 188-196 |
| Toilet Waters | 114, 115 | Alloy, Chromium-Manganese | 194 |
| Tooth Powders | 25 | Electrode Coating | 195 |
| Root Canal Sealer | 67 | Flux, Aluminum | 192 |
| "Toxaphene" Insecticide | 157 | Flux, Aluminum-Silicon | 191 |
| Trade-Mark Chemicals | 365 | Flux, Arc | 191 |
| Transparent Emulsion | 126 | Flux, Boiler Plate | 192 |
| Tranparentizing Oils in Water | 126 | Flux, Magnesium-Zirconium | 193 |
| Tree Defoliant | 164 | Flux, Nickel | 193 |
| Wound Paint | 139 | Flux, Plastic | 193 |
| Troy Weight | 356 | Flux, Steel | 192 |
| Tube Adhesive, Paper | 51 | Point Alloy | 195 |
| | | Soldering Flux | 191 |
| Underwater Cement | 179 | Wire, Aluminum Bronze | 194 |
| Ungreasy Cold Creams | 23 | Wire, Exothermic | 194 |
| Uranium Melting Flux | 194 | Where to Buy Chemicals | 366 |
| Urethane Caulking Compound | 54 | White Shoe Dressing | 30 |
| Foamed | 287 | Window Cleanser | 36 |
| V-Belts | 295 | Wood-Dough Plastic | 34 |
| Valve Lubricant, Plug | 174 | Flour Bleach | 34 |
| Vanishing Creams | 23 | Pulp, Bleaching | 244 |
| Varnish | 217 | Pulp Pitch Formation, | |
| Vegetable Peeling Liquid | 138 | Preventing | 244 |
| Veneer Adhesive | 58 | to Aluminum Adhesive | 52 |
| Vinegar Face Lotion | 17 | Wood's Metal Substitute | 204 |
| Vinyl. See also Polyvinyl Chloride. | | Wool, Antistatic for | 343 |
| Adhesives | 45, 60, 61 | Removal, Hide | 169 |
| Chloride, Adhesive | 60 | Woolens, Spray Printing for | 345 |
| Sheeting | 304 | | |
| -Vinyl Adhesive | 45 | Yarn Lubricant | 345 |
| "Vistanex" Emulsion | 127 | Yeast Defoamer | 130 |
| Vulcanizing Adhesive | 49 | Preservation | 142 |
| | | | |
| Wallpaper Cleaner | 35 | Zinc, Bright Dip for | 201 |
| Paste | 58 | Coating Iron | 181 |
| Remover | 238 | Corrosion Proofing | 186 |
| Wall-Patching Plaster | 33 | Etching | 184 |
| Wash. See Cleaner, Detergent, Soap. | | Zirconium, Electropolishing | 201 |
| | | Magnesium Welding Flux | 193 |

