# The Chemical Formulary

Collection of Commercial Formulas for Making Thousands of products in Many Fields

**VOLUME XXII** 

Editor-in-Chief

H. BENNETT, F.A.I.C.

Director, B. R. Laboratory (Formula Consultants) Mismi Beach, Florida 33140

CHEMICAL PUBLISHING COMPANY, INC.

New York 1979

## The Chemical Formulary, Volume XXII

© 2011 by Chemical Publishing Co., Inc. All rights reserved. This book is protected by copyright. No part of it may be reproduced, stored in a retrieval system or transmitted in any form or by any means; electronic, mechanical, photocopying, recording or otherwise, without the prior written permission of the publisher.

ISBN: 978-0-8206-0280-6

Chemical Publishing Company: www.chemical-publishing.com www.chemicalpublishing.net

© 1979 H. Bennett

First Edition:

© Chemical Publishing Company, Inc. - New York 1979

Second Impression:

**Chemical Publishing Company, Inc. - 2011** 

Printed in the United States of America

## **ABBREVIATIONS**

amp .																																	
amp/d																																	
amp/s																																	
anhyd	T																					•								٠. ٤	inh	ydr	ous
avoir.																														.a	iov	dur	ois
bbl																																.ba	rrel
Be																																Bat	ımé
B.P																													1	bo	ilin	g po	int
°C											. ,															. •		deg	ree	s (	Cen	tigr	ade
cc																												. ci	ubi	ic c	en	time	eter
cd																													cu	rre	nt (	den	sity
cm																																	
cm <sup>3</sup> .																																	
conc .																																	
c.p.																																	
cp																																	
cu ft.																																	
cu in.																																	
cwt.																																	
d																																	
dil																																	
dm																																	
dm <sup>2</sup>																																	
dr																																	
E																																	
°F .														•														deg	Tee	s I	₹ah	reni	heit
ffc .					•	_	_	_			•			•														fre	e f	roi	m c	hlo	rine
ffpa .					•		•			·	•			•	:			•	•	•			•			f	re	e fr	ດກ	ı n	THS	sic a	cid
fl dr																																	
fl oz																																	
ft pt																																	
F.P.																																	
ft																																	
ft <sup>2</sup>																																	
g																																	
g · · · gal	•	•	• •	•	•	•	•	• •	• •	•	•	• •	•	•	•	• •	•	•	•	• •	•	•	•	• (	•	•	•	• •	• •	• •	• •	• 8	100
gr																		٠				٠				٠	٠					. K	lllbi

## **ABBREVIATIONS**

hl hectolite
hr hou
in
kg
1
lb pound
liq
mmete
min
mlmililiter (cubic centimeter)
mm
M.P melting point
N
N.F National Formulary
oz
pH hydrogen-ion concentration
p.p.m
ptpin
pwt pennyweigh
q.s a quantity sufficient to make
qtquanting
r.p.m. revolutions per minute
sec
sp
Sp. Gr
sq. dm square decimeter
tech
tinc
tr
Tw
U.S.P
v
visc
volviscosity
wt
WŁ

#### **CONTRIBUTORS**

Abbott, W. K. I.C.I. Americas Inc. Wilmington, Del. Carlson, B. C. Vanderbilt Co., R.T. Norwalk, Ct. Christensen, E. H. Quaker Oats Co. Chicago, Ill. Witco Chemical Corp. Conte, J. G. Paterson, N.J. Cramer, Marvin B. Goldschmidt Products Corp. White Plains, N.Y. Davis, T. R. Polyesther Corp. Southampton, N.Y. DeBagon, S. A. Amerchol Edison, N.J. DeBeers, Jr. F. M. deBeers Lab. Addison, Ill. Dezeih, C. J. Aloe Creme Labs Ft. Lauderdale, Fla. Doepker, M. L. Consulting Chemist Miami, Fla. France, J. R. Patco Products Co. Kansas City, Mo. Goode, S. R I T A Chemical Corp. Crystal Lake, Ill. Hart, J. Roger W.R. Grace Co. Nashua, N.H. Idson, B. Hoffman LaRoche Inc. Nutley, N.J. Keene, C. N. Monsanto Co. St. Louis, Mo. Leitner, G. J. Stauffer Chemical Co. Dobbs Ferry, N.Y. Mahoney, W. E. Humko Sheffield Lyndhurst, N.J. Meehan, P. P. Sherwin Williams Co. Chicago, Ill. Neulinger, K. F. Croda Inc. New York, N.Y. O'Connor, M. J. Hexcel Fine Organics Lodi, N.J. Patel, S. K. **PVO** International Boonton, N.J. Peterkofsky, Alan L. Alcolac Baltimore, Md. Posselt, F. W. GAF Corp. New York, N.Y. Schmolka, I. R. **BASF** Wyandotte Wyandotte, Mich. Seldner, A. Amerchol Edison, N.J. Slipiec, Roy E. Mazer Chemicals Inc. Gurnec, Ill. Tramel, J. E. Stauffer Chemical Co. Atlanta, Ga. Vaughn, C. D. Kolmar Labs Inc. Port Jervis, N.Y.

#### BOOKS BY H. BENNETT

The Chemical Formulary Vol. I-XXI
The Cumulative Index—The Chemical Formulary
Concise Chemical & Technical Dictionary
New Cosmetic Formulary
Chemical Specialties
Industrial Waxes, Vols. I, II
Practical Emulsions, Vols. I, II
More For Your Money
Trademarks, Chemical

#### **PREFACE**

Chemistry, as taught in our schools and colleges, concerns chiefly synthesis, analysis, and engineering—and properly so. It is part of the right foundation for the education of the chemist.

Many a chemist entering an industry soon finds that most of the products manufactured by his concern are not synthetic or definite chemical compounds, but are mixtures, blends, or highly complex compounds of which he knows little or nothing. The literature in this field, if any, may be meager, scattered, or obsolete.

Even chemists with years of experience in one or more industries spend considerable time and effort in acquainting themselves with any new field which they may enter. Consulting chemists similarly have to solve problems brought to them from industries foreign to them. There was a definite need for an up-to-date compilation of formulae for chemical compounding and treatment. Since the fields to be covered are many and varied, an editorial board of chemists and engineers engaged in many industries was formed.

Many publications, laboratories, manufacturing firms, and individuals have been consulted to obtain the latest and best information. It is felt that the formulas given in this volume will save chemists and allied workers much time and effort.

Manufacturers and sellers of chemicals will find, in these formulae, new uses for their products. Nonchemical executives, professional men, and interested laymen will make through this volume a "speaking acquaint-ance" with products which they may be using, trying, or selling.

It often happens that two individuals using the same ingredients in the same formula get different results. This may be due to slight deviations in the raw materials or unfamiliarity with the intricacies of a new technique. Accordingly, repeated experiments may be necessary to get the best results. Although many of the formulas given are being used commercially, many have been taken from the literature and may be subject to various errors and omissions. This should be taken into consideration. Wherever possible, it is advisable to consult with other chemists or technical workers regarding commercial production. This will save time and money and help avoid

## TABLE OF CONTENTS

I	Introduction1
II	Adhesives41
III	Coatings
ΙV	Cosmetics
V	Detergents and Disinfectants
VI	Drug Products
VII	Elastomers, Plastics and Resins273
VIII	Foods and Beverages
ΙX	Polishes
X	Textile Specialties
ΧI	Miscellaneous
	Appendix353
	Index 378

#### PREFACE TO VOLUME XXII

This new volume of the CHEMICAL FORMULARY series is a collection of new, up-to-date formulas. The only repetitious material is the introduction (Chapter I) which is used in every volume for the benefit of those who may have bought only one volume and who have no educational background or experience in chemical compounding. The simple basic formulas and compounding methods given in the introduction will serve as a guide for beginners and students. It is suggested that they read the introduction carefully and even make a few preparations described there before compounding the more intricate formulas included in the later chapters.

The list of chemicals and their suppliers has been enlarged with new trademark chemicals, so that buying the required ingredients will present no problem.

Grateful acknowledgement is made to the Contributors for their valuable suggestions and contributions.

H. BENNETT

NOTE: All the formulas in Volumes I through XXII (except in the Introduction) are different. Thus, if you do not find what you want in this volume, you may find it in one of the others.

NOTE: This book is the result of cooperation of many chemists and engineers who have given freely of their time and knowledge. It is their business to act as consultants and to give advice on technical matters for a fee. As publishers, we do not maintain a laboratory or consulting service to compete with them. Therefore, please do not ask us for advice or opinions, but consult a chemist.

trouble.

A formula will seldom give exactly the results which one requires. Formulas are useful as starting points from which to work out one's ideas. Also, formulas very often give us ideas which may help us in our specific problems. In a compilation of this kind, errors of omission, commission, and printing may occur. I shall be glad to receive any constructive criticism. Included are the new F.D.A. regulations for drugs, cosmetics, and posticides.

H. BENNETT

#### Chapter I

#### INTRODUCTION

The following introductory matter has been included at the suggestion of teachers of chemistry and home economics.

This section will enable anyone, with or without technical education or experience, to start making simple products without any complicated or expensive machinery. For commercial production, however, suitable equipment is necessary.

Chemical specialties are composed of pigments, gums, resins, solvents, oils, greases, fats, waxes, emulsifying agents, dyestuffs, perfumes, water, and chemicals of great diversity. To compound certain of these with some of the others requires definite and wellstudied procedures, any departure from which will inevitably result in failure. The steps for successful compounding are given with the formulas. Follow them rigorously. If the directions require that (a) is added to (b), carry this out literally, and do not reverse the order. The preparation of an emulsion is often quite as tricky as the making of mayonnaise. In making mayonnaise, you add the oil to the egg, slowly, with constant and even stirring. If you do it correctly, you get mayonnaise. If you depart from any of these details: if you add the egg to the oil, or pour the oil in too quickly, or fail to stir regularly, the result is a complete disappointment. The same disappointment may be expected if the prescribed procedure of any other formulation is violated.

The point next in importance is the scrapulous use of the proper ingredients. Substitutions are sure to result in inferior quality, if not in complete failure. Use what the formula calls for. If a cheaper product is desired, do not prepare it by substituting a cheaper ingredient for the one prescribed: use a different formula. Not infrequently, a formula will call for an ingredient which is difficult to obtain. In such cases, either reject the formula or substitute a similar substance only after a preliminary experiment demonstrates its usability. There is a limit to which this rule may reasonably be extended. In some cases, substitution of an equivalent ingredient may be made legitimately. For example, when the formula calls

for white wax (beeswax), yellow wax can be used, if the color of the finished product is a matter of secondary importance. Yellow beeswax can often replace white beeswax making due allowance for color, but paraffin wax will not replace beeswax, even though its light color seems to place it above yellow beeswax.

This leads to the third point: the use of good-quality ingredients, and ingredients of the correct quality. Ordinary lanolin is not the same thing as anhydrous lanolin. The replacement of one with the other, weight for weight, will give discouragingly different results. Use exactly what the formula calls for: if you are not acquainted with the substance and you are in doubt as to just what is meant, discard the formula and use one you understand. Buy your chemicals from reliable sources. Many ingredients are obtainable in a number of different grades: if the formula does not designate the grade, it is understood that the best grade is to be used. Remember that a formula and the directions can tell you only part of the story. Some skill is often required to attain success. Practice with a small batch in such cases until you are sure of your technique. Many examples can be cited. If the formula calls for steeping quince seed for 30 min in cold water, steeping for 1 hour may yield a mucilage of too thin a consistency. The originator of the formula may have used a fresher grade of seed, or his conception of what "cold" water means may be different from yours. You should have a feeling for the right degree of mucilaginousness, and if steeping the seed for 30 min fails to produce it, steep them longer until you get the right kind of mucilage. If you do not know what the right kind is, you will have to experiment until you find out. This is the reason for the recommendation to make small experimental batches until successful results are obtained. Another case is the use of dyestuffs for coloring lotions and the like. Dyes vary in strength; they are all very powerful in tinting value; it is not always easy to state in quantitative terms how much to use. You must establish the quantity by carefully adding minute quantities until you have the desired tint. Gum tragacanth is one of those products which can give much trouble. It varies widely in solubility and bodying power; the quantity listed in the formula may be entirely unsuitable for your grade of tragacanth. Therefore, correction is necessary, which can be made only after experiments with the available gum.

In short, if you are completely inexperienced, you can profit greatly by experimenting. Such products as mouthwashes, hair tonics, and astringent lotions need little or no experience, because they are, as a rule, merely mixtures of simple liquid and solid ingredients, which dissolve without difficulty and the end product is a clear solution that is ready for use when mixed. However, face creams, toothpastes, lubricating greases, wax polishes, etc., whose formulation requires relatively elaborate procedures and which must have a definte final viscosity, need some skill and not infrequently some experience.

#### **FIGURING**

Some prefer proportions expressed by weight or volume, others use percentages. In different industries and foreign countries different systems of weights and measures are used. For this reason, no one set of units could be satisfactory for everyone. Thus diverse formulas appear with different units, in accordance with their sources of origin. In some cases, parts are given instead of percentage or weight or volume. On the pages preceding the index, conversion tables of weights and measures are listed. These are used for changing from one system to another. The following examples illustrate typical units:

#### **EXAMPLE No. 1**

#### Ink for Marking Glass

Glycerin	40	Ammonium Sulfate	10
Barium Sulfate	15	Oxalic Acid	8
Ammonium Bifluoride	15	Water	12

Here no units are mentioned. In this case, it is standard practice to use parts by weight throughout. Thus here we may use ounces, grams, pounds, or kilograms as desired. But if ounces are used for one item, the ounce must be the unit for all the other in the formula.

#### EXAMPLE No. 2

#### Flexible Glue

Powdered Glue	30.90%	Glycerin	5.15%
Sorbitol (85%)	15.45%	Water	48.50%

Where no units of weight or volume, but percentages are given, forget the percentages and use the same method as given in Example No. 1.

#### Example No. 3

#### Antiseptic Ointment

Petrolatum	16 parts	Benzoic Acid	1 part
Coconut Oil	12 parts	Chlorothymol	1 part
Salicylic Acid	1 part		

The instructions given for Example No. 1 also apply to Example No. 3. In many cases, it is not wise to make up too large a quantity of a product before making a number of small batches to first master the necessary technique and also to see whether the product is suitable for the particular purpose for which it is intended. Since, in many cases, a formula may be given in proportions as made up on a factory scale, it is advisable to reduce the quantities proportionately.

#### EXAMPLE No. 4

#### Neutral Cleansing Cream

Mineral Oil	80 lb	Water	90 lb
Spermaceti	30 lb	Glycerin	10 lb
Glyceryl Monostearate	24 lb	Perfume	To suit

Here, instead of pounds, ounces or even grams may be used. This formula would then read:

Mineral Oil	80 g	Water	90 g
Spermaceti	30 g	Glycerin	10 g
Glyceryl Monostearate	24 g	Perfume	To suit

Reduction in bulk may also be obtained by taking the same fractional part or portion of each ingredient in a formula. Thus in the following formula:

#### Example No. 5

#### Vinegar Face Lotion

Acetic Acid (80%)	20	Alcohol	440
Glycerin	20	Water	500
Perfume	20		

We can divide each amount by ten and then the finished bulk will be only one tenth of the original formula. Thus it becomes:

Acetic Acid (80%)	2	Alcohol	44
Glycerin	2	Water	50
Perfume	2		

#### APPARATUS -

For most preparations, pots, pans, china, and glassware, which are used in every household, will be satisfactory. For making fine mixtures and emulsions, a malted-milk mixer or egg beater is necessary. For weighing, a small, low-priced scale should be purchased from a laboratory-supply house. For measuring fluids, glass graduates or measuring glasses may be purchased from your local druggist. Where a thermometer is necessary, a chemical thermometer should be obtained from a druggist or chemical-supply firm.

#### **METHODS**

To understand better the products which you intend to make, it is advisable that you read the complete section covering such products. You may learn different methods that may be used and also to avoid errors which many beginners are prone to make.

#### CONTAINERS FOR COMPOUNDING

Where discoloration or contamination is to be avoided, as in light-colored, or food and drug products, it is best to use enameled or earthenware vessels. Aluminum is also highly desirable in such cases, but it should not be used with alkalis as these dissolve and corrode aluminum.

#### **HEATING**

To avoid overheating, it is advisable to use a double boiler when temperatures below 212°F (temperature of boiling water) will suffice. If a double boiler is not at hand, any pot may be filled with water and the vessel containing the ingredients to be heated placed in the water. The pot

may then be heated by any flame without fear of overheating. The water in the pot, however, should be replenished from time to time; it must not be allowed to "go dry." To get uniform higher temperatures, oil, grease, or wax is used in the outer container in place of water. Here, of course, care must be taken to stop heating when thick fumes are given off as these are inflammable. When higher uniform temperatures are necessary, molten lead may be used as a heating medium. Of course, with chemicals which melt uniformly and are nonexplosive, direct heating over an open flame is permissible, with stirring, if necessary.

Where instructions indicate working at a certain temperature, it is important to attain the proper temperature not by guesswork, but by the use of a thermometer. Deviations from indicated temperatures will usually result in spoiled preparations.

#### TEMPERATURE MEASUREMENT

In the United States and in Great Britain, the Fahrenheit scale of temperature is used. The temperature of boiling water is 212° Fahrenheit (212°F); the temperature of melting ice is 32° Fahrenheit (32°F).

In scientific work, and in most foreign countries, the Centigrade scale is used, on which the temperature of boiling water is 100° Centigrade (100°C) and the temperature of melting ice is 0° Centigrade (0°C).

The temperature of liquids is measured by a glass thermometer. This is inserted as deeply as possible in the liquid and is moved about until the temperature reading remains steady. It takes a short time for the glass of the thermometer to reach the temperature of the liquid. The thermometer should not be placed against the bottom or side of the container, but near the center of the liquid in the vessel. Since the glass of the thermometer bulb is very thin, it breaks easily when striking it against any hard surface. A cold thermometer should be warmed gradually (by holding it over the surface of a hot liquid) before immersion. Similarly the hot thermometer when taken out of the liquid should not be put into cold water suddenly. A sharp change in temperature will often crack the glass.

#### MIXING AND DISSOLVING

Ordinary dissolution (e.g., that of sugar in water) is hastened by stirring and warming. Where the ingredients are not corrosive, a clean stick, a fork, or spoon may be used as a stirring rod. These may also be used for

mixing thick creams or pastes. In cases where very thorough stirring is necessary (e.g., in making mayonnaise, milky polishes, etc.), an egg beater or a malted-milk mixer is necessary.

#### FILTERING AND CLARIFICATION

When dirt of undissolved particles are present in a liquid, they are removed by settling or filtering. In the first procedure, the solution is allowed to stand and if the particles are heavier than the liquid they will gradually sink to the bottom. The liquid may be poured or siphoned off carefully and, in some cases, it is then sufficiently clear for use. If, however, the particles do not settle out, then they must be filtered off. If the particles are coarse they may be filtered or strained through muslin or other cloth. If they are very small, filter paper is used. Filter papers may be obtained in various degrees of fineness. Coarse filter paper filters rapidly but will not retain extremely fine particles. For fine particles, a very fine grade of filter paper should be used. In extreme cases, even this paper may not be fine enough. Then it will be necessary to add to the liquid 1 to 3% infusorial earth or magnesium carbonate. These are filter aids that clog up the pores of the filter paper and thus reduce their size and hold back undissolved material of extreme fineness. In all such filtering, it is advisable to take the first portions of the filtered liquid and pour them through the filter again as they may develop cloudiness on standing.

#### **DECOLORIZING**

The most commonly used decolorizer is decolorizing carbon. This is added to the liquid to the extent of 1 to 5% and the liquid is heated, with stirring, for ½ hour to as high a temperature as is feasible. The mixture is then allowed to stand for a while and filtered. In some cases, bleaching must be resorted to.

#### **PULVERIZING AND GRINDING**

Large masses or lumps are first broken up by wrapping in a clean cloth, placing between two boards, and pounding with a hammer. The smaller pieces are then pounded again to reduce their size. Finer grinding is done in a mortar with a pestle.

#### SPOILAGE AND LOSS

All containers should be closed when not in use to prevent evaporation or contamination by dust; also because, in some cases, air affects the product adversely. Many chemicals attack or corrode the metal containers in which they are kept. This is particularly true of liquids. Therefore, liquids should be transferred into glass bottles which should be as full as possible. Corks should be covered with aluminum foil (or dipped in melted paraffin wax when alkalies are present).

Glue, gums, olive oil, or other vegetable or animal products may ferment or become rancid. This produces discoloration or unpleasant odors. To avoid this, suitable antiseptics or preservatives must be used. Cleanliness is of utmost importance. All containers must be cleaned thoroughly before use to avoid various complications.

#### **WEIGHING AND MEASURING**

Since, in most cases, small quantities are to be weighed, it is necessary to get a light scale. Heavy scales should not be used for weighing small amounts as they are not accurate enough for this type of weighing.

For measuring volumes of liquids, measuring glasses or cylinders (graduates) should be used. Since this glassware cracks when heated or cooled suddenly it should not be subjected to sudden changes of temperature.

#### **CAUTION**

Some chemicals are corrosive and poisonous. In many they are labeled as such. As a precautionary measure, it is advised not to inhale them and, if smelling is absolutely necessary, only to sniff a few inches from the cork or stopper. Always work in a well-ventilated room when handling poisonous or unknown chemicals. If anything is spilled, it should be wiped off and washed away at once.

#### WHERE TO BUY CHEMICALS AND APPARATUS

Many chemicals and most glassware can be purchased from your druggist. A list of suppliers of all products is at the end of this book.

ı

Acetaminophen Tablet, 258	Atomic Weights, 260
Acne Cream, 245, 246, 260, 261	
Adhesive, 28, 41. Also see Binder,	
Cement, Paste	Baby Powder, 141, 263
Adhesive, Contact, 42	Bakers' Cream Filling, 311
Flame-Retardant, 50	Icing, 311
Hot-Melt, 43	Whipped Topping, 311
Laminating, 44	Baking Powder, 19
Polyvinyl Acetate, 50	Balloons, Toy, 279
Polyvinyl Chloride, 49	Barbecue Sauce, 319
Air Freshener, 351. Also see Deo-	Barium Sulfate Suspension, 265
dorant, Room	Bath, Bubble, 94-96
Advice, 9	Preparations, 94-97
Allergy Relief, 260	Bedbug Exterminator, 18
Aluminum Etch, 350	Beer Pipe Cleaner, 9
Analgesic, 242	Beverage, Cocoa, 300
Anise Flavor, 302	Nutritious, 299
Ant Poison, 18	Orange-Milk, 301
Antacid, Stomach, 250-252	Protein, 299
Antifreeze, Noncorrosive, 345	Synthetic, 297-299
Antiperspirant, 83-90, 176	Bisulfite Gel, Sodium, 351
Antiseptic Gel, 248	Bleach, Cotton, 327
Ointment, 4	Hair, 83
Antistatic Spray, 351	Laundry, 34, 210
Apparatus, 5	Polyester, 327
Where to Buy, 8	Wood Floor, 30
Aquarium Cement, 29	Blemish Masker, 200-203
Aspirin Tablet, 257	Bluing, Laundry, 34
Children, 257	Boiler Compound, 38
Athlete's Foot Remedy, 263	Bottle Protector, Glass, 346
378	,

Bread, Soy Flour, 309	Disinfectant, 239, 240. Also
Sticks, 310	Cleaner Sanitizer
Breath Freshener, 267. Also	Disinfectant Deodorizer, 240
Mouthwash	Dyeing Equipment, 333
Brilliantine, 80	Floor, 233
Briquet Binder, 51	Furniture, 232
Bubble Bath, 94-96	Garage Floor, 233
Burn Cream, 244, 245	Glass, 32, 225, 226, 325
,	Grease, 224
	Hand, 191-193
Cake, Sponge Layer, 310	Hand Surface, 227-229
Calamine Emulsion, 265	Hand Waterless, 237
Callus Softener, 264	Household, 33, 219
Candle Discoloration, Preventing,	Industrial Hand, 217, 218
340	Latrine, 241
Candles, 27	Leather, 224
Canary Food, 26	Milk Pipe, 9
Car Wash, 236	Noncaustic, 220
Caramels, 303	Oven, 237
Caulking Compounds, 41, 42	Paint-Brush, 33
Cautions, 8	Sanitizer, Dairy, 238
Cement Floor Hardener, 28	Hospital, 238
Chemical Container, 291	Industrial, 238
Copper, 235, 324	Spray, 218
Denture, 271, 272	Steam Industrial, 224
Chemicals, Incompatible, 357	Straw, 33
Trademark, 365	Tire, White Wall, 225
Where to Buy, 8, 372	Toilet Bowl, 230
Chest Rub, 16	Vinyl, 224
Chlorpromazine Tablet, 259	Vinyl Auto Top, 225
Chocolate Coating, Milk, 302	Wall, 229
Sugarless, 303	Wallpaper, 32
Clarification, 7	Waterless Hand, 193
Cleaner, Abrasive, 218	Window, 32, 226
Aluminum, 230	Coal Tar Ointment, 264
Beer Pipe, 9	Coating, Electrical Conforming, 53
Borax Compound, 220	Emulsion, 51
Carpet, 223	Coatings, 52, 56, 57
Car Wash, 225	Cocoa Beverage, Synthetic, 298, 299

Butter Replacement, 302	Cricket Control, 338
Powder, 19 Coffee Beverage, Synthetic, 297-	Custard, Eggless, 305
299	Cuticle Cream, 129
Whitener, 313	Remover, 128, 129
Cologne, 123, 124	
Coloring Steel, 22	
Concrete Floor Coating, 59	
Coning Oil, 329	Dandruff, Anti-, 73
Containers, 5	Decolorizing, 7
Copper, Antique Coloring, 21	Defoamer, 344
Antitamish, 349	Denture Cleaner, 271, 272
Cleaner, 235, 324	Deodorant, Body, 91-93
Corn Remover, 264	Room, 17
Cortisone Cream, 248	Deodorizer, Cesspool, 241
Cosmetic Plant Inspection, 376	Toilet Drip, 241
Stick, Emollient, 177	Depilatory, 65-67
Costs, Calculating, 9	Desensitizing Ammonium Nitrate,
Cough-Cold Tablet, 256	346
Crayon, 21	Detergent, All-Purpose, 217
Cream, All-Purpose, 183	Bar, 221
Barrier Skin, 194	Cold Wash Wool, 205
Biostatic Cosmetic, 190	Enzyme, 216
Cleansing, 4, 10, 187-189	Heavy Duty, 211, 214
Cold, 10, 11, 179-182	High Foam, 207
Nongreasy, 11	Light Duty, 213
Cortisone, 248	Low Foam, 207
Cuticle, 129	Nonphosphate, 205, 206
Detergent, 190	Textile Scouring, 328
Hand Protective, 184, 194	Dishwashing Compound, 216, 217,
Moisturizing, 173-177	231
Night, 178, 179	Disinfectant, 17, 241
Nondairy, 313	Dissolving, 6
Powdered Cosmetic, 184	Doughnut Glaze, 308
Roll Massage, 186	Protein, 308
Shaving, 159, 162	Drain Opener, 231
Brushless, 13, 162-164	Dressing, Low Calorie French, 314
Vanishing, 12, 186, 187	Dry Cleaning Fluid, 31, 221
Vitamin, 185	Dust Control, Cotton Mill, 333

Ear Wax Remover, 262 Egg Washing Detergent, 231 Epoxy, Castable, 296 Resins, Solvent for, 295 System, Thickening, 296 Essential Oils, Encapsulating, 341	Fuel Oil Antistatic, 345 Improver, 345 Sludge Disperser, 345 Fumigant, Grain, 339
Solubilizing, 341 Ester Emulsion, Fatty, 344 Ethyl Cellulose, Solvent for, 294 Eye Cream, 151 Highlighter, 151, 153 Makeup Remover, 153 Shadow, 147-150	Gasoline, Solidified, 38 Glass Etch, 23 Glassine Paper, 34 Glazing Adhesive, 49 Glue, Flexible, 3 Glycerin Gel, 143 Grafting Wax, 27 Grain Fumigant, 339 Grease, Graphite, 27 Greaseproofing Paper, 36
Fabric Softener, 329 Face Mask, Cosmetic, 138, 139 Federal Regulations, 353 Feed Binder, 51 Figuring, 3 Filtering, 7 Fire Extinguisher, 37, 38 Kindler, 38 Fireproofing Canvas, 37 Fabrics, 37 Paper, 37 First Aid, 363 Flame Retardants, Textile, 331 Flocking Compound, 331 Fly Bait Poison, 337 Paper, 18 Spray, 16, 17 Foliar Spray, 334 Foot Powder, 15, 262, 263 Freckle Remover, 165	Grinding, 7 Gypsum Board Binder, 51  Hair Bleach, 83 Conditioner, 67-71 Dye, 81, 82 Pomade, 80, 81 Relaxer, 72 Repair, 71 Rinse, 112-114, 117 Setting Compound, 73-76, 114 Shampoo, See Shampoo Spray, 114 Straightener, 79 Thickener, 73 Waving Compound, 77 Heating, 5 Heat Rub, 243, 249
Frozen Foods, Nonstick, 315 Fudge, Chocolate, 304	Ice Cream Sweetener, 313 Incompatible Chemicals, 357

Ink, Heat Transfer Printing, 339 Indelible, 21 Marking Glass, 3 One-Time Carbon Paper, 340 Remover, 34 Solvent for Flexographic, 294 Writing, 26 Insect Repellent, 16, 336, 337 Insecticide, 18 Isosorbide Dinitrate Tablet, 260	Makeup, 196-199 Leg, 199, 200 Remover, 204 Malted Milk Powder, 19 Margarine, Low-Fat, 314 Mascara, 144-146 Measuring, 8 Medicated Rub, 249 Metal Coatings, 57 Coloring, 21, 22 Substrate Removal, 351
Kaolin-Pectin Suspension, 252	Methods, 5 Mildewcide, 333 Mineral Oil Emulsion, 342, 343
Label law, 377	Mixing, 6
Lacquer, 60 Latex. Also see Coating, Paint	Mold Release, 351
Acrylic, 284	Molding Compound, 26, 279
Casting, 285	Mosquito Repellent, 16 Mothproofing, 18, 338
Copolymer, 283	Mouthwash, 14, 265, 266
Polyvinyl Acetate, 282	Mud Pack, 137
Leather Preservative, 24	Multivitamin Tablet, 254
Leg Makeup, 199, 200	
Lemon Extract, 20 Liniment, 15	
Lip Balm, Sunscreen, 134	
Gloss, 133, 134	Nail Conditioner, 126
Rouge, 131	Hardener, 127
Lipstick, 134-137	Polish, 127
Lotion, Astringent, 164, 165	Polish Remover, 128
Baby, 167	Newspapers, Preserving, 340
Cosmetic, 167-171 Face, 4	Nitrocellulose, Solvent for, 295
Hand, 12	Nut Protective Coating, 305
Poison Ivy, 262	
Shave, After-, 156-159	
Lubricants, 26	
Emulsion, 242	Oilproofing Paper, 36
Metal Forming, 351	Opthalmic Gel, 248

Paint. Also see Coatings Acrylic, 55 Butadiene-Styrene, 53 Polyvinyl Acetate, 54 Remover, 30, 33, 63, 234 Tempera, 61	Primer, Metal, 58 Psoriasis Cream, 247 Pulverizing, 7 Putty, 29
PAS Tablet, 259 Pavement, Highway, 346 Pellet Binder, 51 Penetrating Oil, 26 Penicillin V-Potassium Tablet, 259 Perfume, Roll-On, 123 Peroxide Gel, Hydrogen, 143 Pesticide, 334-336 Pet Grooming Compounds, 121, 122	Raisin Protective Coating, 305 Rat Biscuit, 339 Reading, Useful, 9 Refrigerator Coil Icing Removal, 345 Resins, Solvents for, 294 Roach Killer, 338 Rouge, 129, 130
Phenobarbital Tablet, 258 Photographic Solutions, 39, 40 Phytocosmetic Emulsion, 144 Pie Crust, 311 Pigment Paste, 54 Plaster, Wall Patching, 28 Plastic, Conduit, 289	Lip, 131 "Rubber," Automotive Cellular Extrusions, 273  Bands, 281  Foam, 274  Microcellular, 273  Sponge, 274–278
Flameproof, 286-288 Pressure Pipe, 288 Sewer Pipe, 289	Rug Shampoo, 221 Rust Inhibitor, Water, 350 Remover, 34
Poison Ivy Lotion, 262 Polish, Auto, 25, 317-320 Boat, 320 Floor, 25, 320-322 Furniture, 322-324 Metal, 22	Rusted Parts, Loosening, 26 Rustproofing, 22
Notes, 24 Shoe, 24, 326 Wood, 324	Sachet, 124, 125 Scouring Powder, 232 Sealant, Architectural, 45
Polybutene Emulsion, 282 Polymers, Solvents for, 292	Nondrying, 48 Tape, Automotive, 46, 47

Shampoo, Baby, 118	Hard Candy, 303		
Conditioner, 115, 116	Jelly, 306		
Egg, 118, 119	Sulfa Suspension, Triple, 252		
Hair, 105-111	Sun Screen, 99-102		
Herbal, 119	Suppository Base, 245		
Oily Hair, 120	Surgical Scrub, 250		
Olive Oil-Vitamin, 119	Sweeping Compound, 234		
Pet, 121, 122	Syrup, Butterscotch, 301		
Rug, 221	Chocolate, 301		
Shave Lotion, After-, 156-159	•		
Pre-Electric, 154-156			
Shaving Cream, 159, 162	Tables, 358, 359		
Brushless, 13, 162-164	Talcum Powder, 98, 140, 141		
Sherbert, 313	Tarnish Remover, 350		
Shoe Dressing, White, 23	Tea, Synthetic, 298		
Polish, 24	Temperature Measurement, 6		
Waterproofing, 23	Termite Control, 338		
Skin Bleach, 165, 166	Textile, Flame Retardants, 331		
Freshener, 172, 173	Finishes, 328-330		
Tanning, 102-104	Scouring Detergent, 328		
Tint, 131–133	Tire Cleaner, White Wall, 225		
Slimming Beverage, 265	Tobacco, Removing Toxic Gases		
Snuff, Tobaccoless, 348	from Smoking, 347		
Soap. Also see Cleaner, Detergent	Tooth Paste, 267-270		
Emollient, 196	Powder, 14		
Liquid, 30, 195	Triglyceride Emulsion, 344		
Mechanics' Hand, 31			
Notes, 30			
Saddle, 31	Upholstery Shampoo, 221		
Toilet, 141–143			
Soldering Flux, 39			
Solubilizing Oils, 341	Vanilla Flavor, 20		
Solvent Evaporation Time, 64 Solvents for Plastics Elastomers, 293	Vegetable Oil Emulsion, 341		
	Vinyl Compounds, Solvent for, 295		
Spoilage, 8	House Siding, 289		
Spot Remover, 33, 222	Plastisol, 290		
Sugarless, Baked Goods, 306–308	Vitamin B <sub>1</sub> Tablet, 253		
Chocolate, 303	C Tablet, 256		
Dessert, 306	E Products, 253		

```
Wallpaper Paste, 28
Wall Patching Plaster, 28
Wash-Wear Process, 328
Watch Dial Finish, 60
Waterproofing Canvas, 36
   Fiberboard, 35
   Paper, 35
   Shoes, 23
   Wood, 35
Water Softener, 234
Wax Emulsion, 340, 341
   Investment Casting, 340
   Polish. See Polish
   Remover, 234, 322
Weighing, 8
Wood Dough Plastic, 29
   Stains, 62
Wood Preservative, 346
```